

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
2 3/8"	4.60	J-55	4.430	0.190	1.901	1.311	1.986	68.0%	70.1%	3.334	49,000	7,300	65,300
2 3/8"	4.60	L-80	4.430	0.190	1.901	1.311	1.986	68.0%	70.1%	3.334	71,300	10,700	83,600
2 3/8"	4.60	T-95	4.430	0.190	1.901	1.311	1.986	68.0%	70.1%	3.334	84,700	12,700	92,900
2 3/8"	4.60	P-110	4.430	0.190	1.901	1.311	1.986	68.0%	70.1%	3.334	98,100	14,700	110,300
2 3/8"	4.60	Q-125	4.430	0.190	1.901	1.311	1.986	68.0%	70.1%	3.334	111,500	16,700	119,700
2 3/8"	5.80	J-55	5.750	0.254	1.773	1.702	1.858	69.0%	71.1%	4.087	64,600	7,400	86,000
2 3/8"	5.80	L-80	5.750	0.254	1.773	1.702	1.858	69.0%	71.1%	4.087	93,900	10,800	110,100
2 3/8"	5.80	T-95	5.750	0.254	1.773	1.702	1.858	69.0%	71.1%	4.087	111,500	12,900	122,300
2 3/8"	5.80	P-110	5.750	0.254	1.773	1.702	1.858	69.0%	71.1%	4.087	129,200	14,900	145,300
2 3/8"	5.80	Q-125	5.750	0.254	1.773	1.702	1.858	69.0%	71.1%	4.087	146,800	17,000	157,600
2 7/8"	6.40	J-55	6.160	0.217	2.347	1.822	2.434	66.0%	68.0%	3.383	66,100	7,100	87,500
2 7/8"	6.40	L-80	6.160	0.217	2.347	1.822	2.434	66.0%	68.0%	3.383	96,200	10,400	112,200
2 7/8"	6.40	T-95	6.160	0.217	2.347	1.822	2.434	66.0%	68.0%	3.383	114,300	12,300	124,900

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
2 7/8"	6.40	P-110	6.160	0.217	2.347	1.822	2.434	66.0%	68.0%	3.383	132,300	14,300	148,200
2 7/8"	6.40	Q-125	6.160	0.217	2.347	1.822	2.434	66.0%	68.0%	3.383	150,400	16,200	160,900
2 7/8"	7.80	J-55	7.660	0.276	2.798	2.266	2.310	69.0%	71.1%	3.371	85,900	7,400	113,700
2 7/8"	7.80	L-80	7.660	0.276	2.798	2.266	2.310	69.0%	71.1%	3.371	125,000	10,800	145,800
2 7/8"	7.80	T-95	7.660	0.276	2.798	2.266	2.310	69.0%	71.1%	3.371	148,500	12,900	162,300
2 7/8"	7.80	P-110	7.660	0.276	2.798	2.266	2.310	69.0%	71.1%	3.371	171,900	14,900	192,700
2 7/8"	7.80	Q-125	7.660	0.276	2.798	2.266	2.310	69.0%	71.1%	3.371	195,400	17,000	209,100
2 7/8"	8.60	J-55	8.440	0.308	2.229	2.498	2.265	70.0%	72.1%	3.706	96,100	7,500	127,300
2 7/8"	8.60	L-80	8.440	0.308	2.229	2.498	2.265	70.0%	72.1%	3.706	139,900	11,000	163,100
2 7/8"	8.60	T-95	8.440	0.308	2.229	2.498	2.265	70.0%	72.1%	3.706	166,100	13,100	181,500
2 7/8"	8.60	P-110	8.440	0.308	2.229	2.498	2.265	70.0%	72.1%	3.706	192,300	15,100	215,600
2 7/8"	8.60	Q-125	8.440	0.308	2.229	2.498	2.265	70.0%	72.1%	3.706	218,600	17,200	234,000
3 1/2"	9.20	J-55	8.810	0.254	2.867	2.604	2.981	64.0%	66.0%	3.608	91,700	6,900	120,300

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
3 1/2"	9.20	L-80	8.810	0.254	2.867	2.604	2.981	64.0%	66.0%	3.608	133,400	10,000	154,600
3 1/2"	9.20	T-95	8.810	0.254	2.867	2.604	2.981	64.0%	66.0%	3.608	158,400	11,900	172,400
3 1/2"	9.20	P-110	8.810	0.254	2.867	2.604	2.981	64.0%	66.0%	3.608	183,400	13,800	204,500
3 1/2"	9.20	Q-125	8.810	0.254	2.867	2.604	2.981	64.0%	66.0%	3.608	208,400	15,700	222,200
3 1/2"	10.20	J-55	9.910	0.289	2.797	2.931	2.911	66.0%	68.0%	4.11	106,400	7,100	139,600
3 1/2"	10.20	L-80	9.910	0.289	2.797	2.931	2.911	66.0%	68.0%	4.11	154,800	10,400	179,500
3 1/2"	10.20	T-95	9.910	0.289	2.797	2.931	2.911	66.0%	68.0%	4.11	183,800	12,300	200,000
3 1/2"	10.20	P-110	9.910	0.289	2.797	2.931	2.911	66.0%	68.0%	4.11	212,900	14,300	237,400
3 1/2"	10.20	Q-125	9.910	0.289	2.797	2.931	2.911	66.0%	68.0%	4.11	241,900	16,200	257,900
3 1/2"	12.70	J-55	12.520	0.375	2.625	3.702	2.739	69.0%	71.1%	4.176	140,400	7,400	184,300
3 1/2"	12.70	L-80	12.520	0.375	2.625	3.702	2.739	69.0%	71.1%	4.176	204,300	10,800	236,900
3 1/2"	12.70	T-95	12.520	0.375	2.625	3.702	2.739	69.0%	71.1%	4.176	242,600	12,900	264,000
3 1/2"	12.70	P-110	12.520	0.375	2.625	3.702	2.739	69.0%	71.1%	4.176	280,900	14,900	313,300
3 1/2"	12.70	Q-125	12.520	0.375	2.625	3.702	2.739	69.0%	71.1%	4.176	319,200	16,900	340,400

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
3 1/2"	15.80	J-55	15.370	0.476	2.432	4.548	2.537	75.0%	77.2%	4.345	187,500	8,100	246,100
3 1/2"	15.80	L-80	15.370	0.476	2.432	4.548	2.537	75.0%	77.2%	4.345	272,700	11,800	316,300
3 1/2"	15.80	T-95	15.370	0.476	2.432	4.548	2.537	75.0%	77.2%	4.345	323,900	14,000	352,500
3 1/2"	15.80	P-110	15.370	0.476	2.432	4.548	2.537	75.0%	77.2%	4.345	375,000	16,200	418,300
3 1/2"	15.80	Q-125	15.370	0.476	2.432	4.548	2.537	75.0%	77.2%	4.345	426,200	18,400	454,500
4"	9.50	J-55	9.110	0.226	3.423	2.694	3.539	65.0%	67.0%	3.437	96,300	7,000	125,400
4"	9.50	L-80	9.110	0.226	3.423	2.694	3.539	65.0%	67.0%	3.437	140,100	10,200	161,600
4"	9.50	T-95	9.110	0.226	3.423	2.694	3.539	65.0%	67.0%	3.437	166,400	12,100	180,400
4"	9.50	P-110	9.110	0.226	3.423	2.694	3.539	65.0%	67.0%	3.437	192,600	1,400	213,900
4"	9.50	Q-125	9.110	0.226	3.423	2.694	3.539	65.0%	67.0%	3.437	218,900	16,000	232,700
4"	10.70	J-55	10.460	0.262	3.351	3.093	3.467	65.0%	66.9%	3.77	110,500	7,000	143,900
4"	10.70	L-80	10.460	0.262	3.351	3.093	3.467	65.0%	66.9%	3.77	160,800	10,200	185,500
4"	10.70	T-95	10.460	0.262	3.351	3.093	3.467	65.0%	66.9%	3.77	190,900	12,100	207,000

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
4"	10.70	P-110	10.460	0.262	3.351	3.093	3.467	65.0%	66.9%	3.77	221,100	14,000	245,500
4"	10.70	Q-125	10.460	0.262	3.351	3.093	3.467	65.0%	66.9%	3.77	251,200	16,000	267,000
4"	11.60	J-55	11.340	0.286	3.303	3.355	3.419	68.0%	70.1%	3.451	125,500	7,300	163,400
4"	11.60	L-80	11.340	0.286	3.303	3.355	3.419	68.0%	70.1%	3.451	182,600	10,700	210,600
4"	11.60	T-95	11.340	0.286	3.303	3.355	3.419	68.0%	70.1%	3.451	216,800	12,700	235,100
4"	11.60	P-110	11.340	0.286	3.303	3.355	3.419	68.0%	70.1%	3.451	251,000	14,700	278,800
4"	11.60	Q-125	11.340	0.286	3.303	3.355	3.419	68.0%	70.1%	3.451	285,300	16,700	303,200
4"	13.20	J-55	12.930	0.330	3.215	3.826	3.330	70.0%	72.1%	3.984	147,300	7,500	191,800
4"	13.20	L-80	12.930	0.330	3.215	3.826	3.330	70.0%	72.1%	3.984	214,200	11,000	247,200
4"	13.20	T-95	12.930	0.330	3.215	3.826	3.330	70.0%	72.1%	3.984	254,400	13,100	275,800
4"	13.20	P-110	12.930	0.330	3.215	3.826	3.330	70.0%	72.1%	3.984	294,600	15,100	327,100
4"	13.20	Q-125	12.930	0.330	3.215	3.826	3.330	70.0%	72.1%	3.984	334,700	17,200	355,800
4"	16.10	J-55	15.890	0.415	3.045	4.700	3.161	74.0%	76.2%	4.463	191,300	8,000	249,200
4"	16.10	L-80	15.890	0.415	3.045	4.700	3.161	74.0%	76.2%	4.463	278,200	11,600	321,100

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
4"	16.10	T-95	15.890	0.415	3.045	4.700	3.161	74.0%	76.2%	4.463	330,400	13,800	358,300
4"	16.10	P-110	15.890	0.415	3.045	4.700	3.161	74.0%	76.2%	4.463	382,600	16,000	425,000
4"	16.10	Q-125	15.890	0.415	3.045	4.700	3.161	74.0%	76.2%	4.463	434,800	18,200	462,200

4 1/2"	10.50	J-55	10.230	0.224	3.927	3.025	4.045	64.0%	65.9%	3.427	106,400	6,900	137,600
4 1/2"	10.50	L-80	10.230	0.224	3.927	3.025	4.045	64.0%	65.9%	3.427	154,800	10,000	177,700
4 1/2"	10.50	T-95	10.230	0.224	3.927	3.025	4.045	64.0%	65.9%	3.427	183,833	11,900	198,600
4 1/2"	10.50	P-110	10.230	0.224	3.927	3.025	4.045	64.0%	65.9%	3.427	212,900	13,800	235,400
4 1/2"	10.50	Q-125	10.230	0.224	3.927	3.025	4.045	64.0%	65.9%	3.427	241,900	15,700	256,300
4 1/2"	11.60	J-55	11.350	0.250	3.875	3.356	3.993	65.0%	67.0%	3.731	120,000	7,000	155,100
4 1/2"	11.60	L-80	11.350	0.250	3.875	3.356	3.993	65.0%	67.0%	3.731	174,600	10,200	200,400
4 1/2"	11.60	T-95	11.350	0.250	3.875	3.356	3.993	65.0%	67.0%	3.731	207,300	12,100	224,000
4 1/2"	11.60	P-110	11.350	0.250	3.875	3.356	3.993	65.0%	67.0%	3.731	240,100	14,100	265,500
4 1/2"	11.60	Q-125	11.350	0.250	3.875	3.356	3.993	65.0%	67.0%	3.731	272,800	16,000	289,000

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
4 1/2"	13.50	J-55	13.040	0.290	3.795	3.858	3.913	66.0%	68.0%	4.183	139,900	7,100	180,900
4 1/2"	13.50	L-80	13.040	0.290	3.795	3.858	3.913	66.0%	68.0%	4.183	203,500	10,400	233,700
4 1/2"	13.50	T-95	13.040	0.290	3.795	3.858	3.913	66.0%	68.0%	4.183	241,700	12,300	261,100
4 1/2"	13.50	P-110	13.040	0.290	3.795	3.858	3.913	66.0%	68.0%	4.183	279,900	14,300	309,500
4 1/2"	13.50	Q-125	13.040	0.290	3.795	3.858	3.913	66.0%	68.0%	4.183	318,000	16,200	337,000
4 1/2"	15.10	J-55	14.980	0.337	3.701	4.431	3.819	71.0%	73.0%	4.223	173,000	7,600	223,700
4 1/2"	15.10	L-80	14.980	0.337	3.701	4.431	3.819	71.0%	73.0%	4.223	251,700	11,200	289,000
4 1/2"	15.10	T-95	14.980	0.337	3.701	4.431	3.819	71.0%	73.0%	4.223	298,900	13,300	323,000
4 1/2"	15.10	P-110	14.980	0.337	3.701	4.431	3.819	71.0%	73.0%	4.223	346,100	15,400	382,800
4 1/2"	15.10	Q-125	14.980	0.337	3.701	4.431	3.819	71.0%	73.0%	4.223	393,300	17,500	416,800
4 1/2"	16.60	J-55	16.520	0.375	3.625	4.886	3.743	74.0%	76.2%	4.135	1,044,400	8,000	1,173,000
4 1/2"	16.60	L-80	16.520	0.375	3.625	4.886	3.743	74.0%	76.2%	4.135	1,519,100	11,600	1,589,300
4 1/2"	16.60	T-95	16.520	0.375	3.625	4.886	3.743	74.0%	76.2%	4.135	1,804,000	13,800	1,822,400
4 1/2"	16.60	P-110	16.520	0.375	3.625	4.886	3.743	74.0%	76.2%	4.135	2,088,800	16,000	2,138,600

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
4 1/2"	16.60	Q-125	16.520	0.375	3.625	4.886	3.743	74.0%	76.2%	4.135	2,373,700	18,200	2,371,700

5"	13.00	J-55	12.830	0.253	4.369	3.930	4.489	65.0%	66.9%	4.219	135,500	7,000	173,900
5"	13.00	L-80	12.830	0.253	4.369	3.930	4.489	65.0%	66.9%	4.219	197,100	10,200	225,100
5"	13.00	T-95	12.830	0.253	4.369	3.930	4.489	65.0%	66.9%	4.219	234,100	12,100	252,000
5"	13.00	P-110	12.830	0.253	4.369	3.930	4.489	65.0%	66.9%	4.219	271,000	14,000	298,500
5"	13.00	Q-125	12.830	0.253	4.369	3.930	4.489	65.0%	66.9%	4.219	308,000	16,000	325,300
5"	15.00	J-55	14.870	0.296	4.283	4.398	4.403	65.0%	66.9%	4.412	157,100	7,000	201,700
5"	15.00	L-80	14.870	0.296	4.283	4.398	4.403	65.0%	66.9%	4.412	228,600	10,200	261,200
5"	15.00	T-95	14.870	0.296	4.283	4.398	4.403	65.0%	66.9%	4.412	271,400	12,100	292,200
5"	15.00	P-110	14.870	0.296	4.283	4.398	4.403	65.0%	66.9%	4.412	314,300	14,000	346,200
5"	15.00	Q-125	14.870	0.296	4.283	4.398	4.403	65.0%	66.9%	4.412	357,100	16,000	377,300
5"	18.00	J-55	17.930	0.362	4.151	5.303	4.271	71.0%	73.1%	4.429	207,000	7,600	265,800
5"	18.00	L-80	17.930	0.362	4.151	5.303	4.271	71.0%	73.1%	4.429	301,200	11,100	344,100



# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
5"	18.00	T-95	17.930	0.362	4.151	5.303	4.271	71.0%	73.1%	4.429	357,700	13,200	385,100
5"	18.00	P-110	17.930	0.362	4.151	5.303	4.271	71.0%	73.1%	4.429	414,100	15,300	456,200
5"	18.00	Q-125	17.930	0.362	4.151	5.303	4.271	71.0%	73.1%	4.429	470,600	17,400	497,200
5"	20.30	J-55	20.010	0.408	4.059	5.918	4.179	73.0%	75.2%	4.624	237,600	7,900	305,000
5"	20.30	L-80	20.010	0.408	4.059	5.918	4.179	73.0%	75.2%	4.624	345,600	11,500	394,900
5"	20.30	T-95	20.010	0.408	4.059	5.918	4.179	73.0%	75.2%	4.624	410,400	13,600	441,800
5"	20.30	P-110	20.010	0.408	4.059	5.918	4.179	73.0%	75.2%	4.624	475,200	15,800	523,500
5"	20.30	Q-125	20.010	0.408	4.059	5.918	4.179	73.0%	75.2%	4.624	540,000	17,900	570,400
5"	21.40	J-55	21.300	0.437	4.001	6.299	4.121	75.0%	77.3%	4.781	259,800	8,100	333,000
5"	21.40	L-80	21.300	0.437	4.001	6.299	4.121	75.0%	77.3%	4.781	378,000	11,800	431,500
5"	21.40	T-95	21.300	0.437	4.001	6.299	4.121	75.0%	77.3%	4.781	448,800	14,000	483,000
5"	21.40	P-110	21.300	0.437	4.001	6.299	4.121	75.0%	77.3%	4.781	519,700	16,200	572,200
5"	21.40	Q-125	21.300	0.437	4.001	6.299	4.121	75.0%	77.3%	4.781	590,600	18,400	623,800
5"	23.20	J-55	23.080	0.478	3.919	6.828	4.039	76.0%	78.2%	4.584	285,200	8,200	366,300

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
5"	23.20	L-80	23.080	0.478	3.919	6.828	4.039	76.0%	78.2%	4.584	414,900	11,900	474,200
5"	23.20	T-95	23.080	0.478	3.919	6.828	4.039	76.0%	78.2%	4.584	492,700	14,200	530,500
5"	23.20	P-110	23.080	0.478	3.919	6.828	4.039	76.0%	78.2%	4.584	570,500	16,400	628,600
5"	23.20	Q-125	23.080	0.478	3.919	6.828	4.039	76.0%	78.2%	4.584	648,300	18,700	685,000
5"	24.10	J-55	24.300	0.500	3.875	7.108	3.995	77.0%	79.4%	4.748	301,200	8,300	386,700
5"	24.10	L-80	24.300	0.500	3.875	7.108	3.995	77.0%	79.4%	4.748	438,100	12,100	5,000,600
5"	24.10	T-95	24.300	0.500	3.875	7.108	3.995	77.0%	79.4%	4.748	520,200	14,400	560,100
5"	24.10	P-110	24.300	0.500	3.875	7.108	3.995	77.0%	79.4%	4.748	602,400	16,700	663,600
5"	24.10	Q-125	24.300	0.500	3.875	7.108	3.995	77.0%	79.4%	4.748	684,500	18,900	723,100
5 1/2"	15.50	J-55	15.350	0.275	4.825	4.538	4.947	64.0%	64.9%	3.731	159,700	6,900	203,600
5 1/2"	15.50	L-80	15.350	0.275	4.825	4.538	4.947	64.0%	64.9%	3.731	232,400	10,000	264,200
5 1/2"	15.50	T-95	15.350	0.275	4.825	4.538	4.947	64.0%	64.9%	3.731	275,900	11,900	296,000
5 1/2"	15.50	P-110	15.350	0.275	4.825	4.538	4.947	64.0%	64.9%	3.731	319,500	13,800	350,500

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
5 1/2"	15.50	Q-125	15.350	0.275	4.825	4.538	4.947	64.0%	64.9%	3.731	363,100	15,700	382,300
5 1/2"	17.00	J-55	16.870	0.304	4.767	4.989	4.889	65.0%	66.9%	4.106	178,200	7,000	227,100
5 1/2"	17.00	L-80	16.870	0.304	4.767	4.989	4.889	65.0%	66.9%	4.106	259,200	10,200	294,700
5 1/2"	17.00	T-95	16.870	0.304	4.767	4.989	4.889	65.0%	66.9%	4.106	307,800	12,100	330,300
5 1/2"	17.00	P-110	16.870	0.304	4.767	4.989	4.889	65.0%	66.9%	4.106	356,500	14,000	391,100
5 1/2"	17.00	Q-125	16.870	0.304	4.767	4.989	4.889	65.0%	66.9%	4.106	405,100	1,600	426,600
5 1/2"	20.00	J-55	19.810	0.361	4.653	5.859	4.775	66.0%	68.0%	3.813	212,600	7,100	271,100
5 1/2"	20.00	L-80	19.810	0.361	4.653	5.859	4.775	66.0%	68.0%	3.813	309,200	10,400	351,700
5 1/2"	20.00	T-95	19.810	0.361	4.653	5.859	4.775	66.0%	68.0%	3.813	367,200	12,300	394,000
5 1/2"	20.00	P-110	19.810	0.361	4.653	5.859	4.775	66.0%	68.0%	3.813	425,200	14,300	433,300
5 1/2"	20.00	Q-125	19.810	0.361	4.653	5.859	4.775	66.0%	68.0%	3.813	483,200	16,200	509,000
5 1/2"	23.00	J-55	22.540	0.415	5.545	6.665	4.667	69.0%	71.0%	4.022	252,800	7,400	322,400
5 1/2"	23.00	L-80	22.540	0.415	5.545	6.665	4.667	69.0%	71.0%	4.022	367,700	10,800	418,300
5 1/2"	23.00	T-95	22.540	0.415	5.545	6.665	4.667	69.0%	71.0%	4.022	436,700	12,900	468,600

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
5 1/2"	23.00	P-110	22.540	0.415	5.545	6.665	4.667	69.0%	71.0%	4.022	505,700	14,900	554,900
5 1/2"	23.00	Q-125	22.540	0.415	5.545	6.665	4.667	69.0%	71.0%	4.022	574,600	16,900	605,200
5 1/2"	26.00	J-55	25.540	0.476	4.423	4.554	4.545	73.0%	75.2%	4.817	303,200	7,900	386,600
5 1/2"	26.00	L-80	25.540	0.476	4.423	4.554	4.545	73.0%	75.2%	4.817	441,000	11,500	501,600
5 1/2"	26.00	T-95	25.540	0.476	4.423	4.554	4.545	73.0%	75.2%	4.817	523,700	13,600	562,000
5 1/2"	26.00	P-110	25.540	0.476	4.423	4.554	4.545	73.0%	75.2%	4.817	363,400	15,800	665,500
5 1/2"	26.00	Q-125	25.540	0.476	4.423	4.554	4.545	73.0%	75.2%	4.817	689,100	17,900	725,900
5 1/2"	26.80	J-55	26.700	0.500	4.375	7.897	4.497	74.0%	76.6%	4.468	321,500	8,000	410,000
5 1/2"	26.80	L-80	26.700	0.500	4.375	7.897	4.497	74.0%	76.6%	4.468	167,700	11,600	231,900
5 1/2"	26.80	T-95	26.700	0.500	4.375	7.897	4.497	74.0%	76.6%	4.468	555,400	13,800	595,900
5 1/2"	26.80	P-110	26.700	0.500	4.375	7.897	4.497	74.0%	76.6%	4.468	643,100	16,000	705,700
5 1/2"	26.80	Q-125	26.700	0.500	4.375	7.897	4.497	74.0%	76.6%	4.468	730,800	18,200	769,700
5 1/2"	29.70	J-55	29.640	0.562	4.251	8.767	4.373	76.0%	78.3%	5.044	366,300	8,200	467,200
5 1/2"	29.70	L-80	29.640	0.562	4.251	8.767	4.373	76.0%	78.3%	5.044	532,900	11,900	606,100

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
5 1/2"	29.70	T-95	29.640	0.562	4.251	8.767	4.373	76.0%	78.3%	5.044	632,800	14,200	679,000
5 1/2"	29.70	P-110	29.640	0.562	4.251	8.767	4.373	76.0%	78.3%	5.044	732,700	16,400	804,100
5 1/2"	29.70	Q-125	29.640	0.562	4.251	8.767	4.373	76.0%	78.3%	5.044	832,600	18,700	877,000
6 5/8"	24.00	J-55	23.580	0.352	5.796	6.974	5.923	66.0%	68.0%	3.909	253,000	7,100	317,200
6 5/8"	24.00	L-80	23.580	0.352	5.796	6.974	5.923	66.0%	68.0%	3.909	368,100	10,400	413,900
6 5/8"	24.00	T-95	23.580	0.352	5.796	6.974	5.923	66.0%	68.0%	3.909	437,100	12,300	465,100
6 5/8"	24.00	P-110	23.580	0.352	5.796	6.974	5.923	66.0%	68.0%	3.909	506,100	14,300	550,100
6 5/8"	24.00	Q-125	23.580	0.352	5.796	6.974	5.923	66.0%	68.0%	3.909	575,100	16,200	601,400
7"	23.00	J-55	22.630	0.317	6.241	6.690	6.369	64.0%	65.9%	4.092	235,600	6,900	293,700
7"	23.00	L-80	22.630	0.317	6.241	6.690	6.369	64.0%	65.9%	4.092	342,800	10,000	348,000
7"	23.00	T-95	22.630	0.317	6.241	6.690	6.369	64.0%	65.9%	4.092	407,000	11,900	432,000
7"	23.00	P-110	22.630	0.317	6.241	6.690	6.369	64.0%	65.9%	4.092	471,300	13,800	510,700

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
7"	23.00	Q-125	22.630	0.317	6.241	6.690	6.369	64.0%	65.9%	4.092	535,600	15,700	558,700
7"	26.00	J-55	25.660	0.362	0.615	7.589	6.279	68.0%	70.0%	4.084	283,600	7,300	353,500
7"	26.00	L-80	25.660	0.362	0.615	7.589	6.279	68.0%	70.0%	4.084	412,500	10,700	462,100
7"	26.00	T-95	25.660	0.362	0.615	7.589	6.279	68.0%	70.0%	4.084	489,900	12,700	519,900
7"	26.00	P-110	25.660	0.362	0.615	7.589	6.279	68.0%	70.0%	4.084	567,300	14,700	614,700
7"	26.00	Q-125	25.660	0.362	0.615	7.589	6.279	68.0%	70.0%	4.084	644,600	16,700	672,400
7"	29.00	J-55	28.720	0.408	6.059	8.494	6.187	69.0%	71.1%	4.656	322,300	7,400	401,900
7"	29.00	L-80	28.720	0.408	6.059	8.494	6.187	69.0%	71.1%	4.656	468,800	10,800	525,300
7"	29.00	T-95	28.720	0.408	6.059	8.494	6.187	69.0%	71.1%	4.656	556,700	12,900	590,900
7"	29.00	P-110	28.720	0.408	6.059	8.494	6.187	69.0%	71.1%	4.656	644,711	14,900	698,600
7"	29.00	Q-125	28.720	0.408	6.059	8.494	6.187	69.0%	71.1%	4.656	732,600	17,000	764,200
7"	32.00	J-55	31.670	0.453	0.600	9.367	6.103	72.0%	74.2%	4.667	370,900	7,800	462,500
7"	32.00	L-80	31.670	0.453	0.600	9.367	6.103	72.0%	74.2%	4.667	539,500	11,300	604,500
7"	32.00	T-95	31.670	0.453	0.600	9.367	6.103	72.0%	74.2%	4.667	640,700	13,400	680,000

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
7"	32.00	P-110	31.670	0.453	0.600	9.367	6.103	72.0%	74.2%	4.667	741,900	15,600	804,000
7"	32.00	Q-125	31.670	0.453	0.600	9.367	6.103	72.0%	74.2%	4.667	843,100	17,700	879,500
7"	35.00	J-55	34.580	0.498	5.879	10.227	6.007	74.0%	76.2%	5.186	416,200	8,000	519,000
7"	35.00	L-80	34.580	0.498	5.879	10.227	6.007	74.0%	76.2%	5.186	605,400	11,600	678,300
7"	35.00	T-95	34.580	0.498	5.879	10.227	6.007	74.0%	76.2%	5.186	718,900	13,800	763,100
7"	35.00	P-110	34.580	0.498	5.879	10.227	6.007	74.0%	76.2%	5.186	832,400	16,000	902,100
7"	35.00	Q-125	34.580	0.498	5.879	10.227	6.007	74.0%	76.2%	5.186	946,000	18,200	986,900
7"	38.00	J-55	37.260	0.540	5.795	11.019	5.923	75.0%	77.2%	4.912	454,200	8,100	566,500
7"	38.00	L-80	37.260	0.540	5.795	11.019	5.923	75.0%	77.2%	4.912	660,700	11,800	743,000
7"	38.00	T-95	37.260	0.540	5.795	11.019	5.923	75.0%	77.2%	4.912	784,600	14,000	832,800
7"	38.00	P-110	37.260	0.540	5.795	11.019	5.923	75.0%	77.2%	4.912	908,500	16,200	984,600
7"	38.00	Q-125	37.260	0.540	5.795	11.019	5.923	75.0%	77.2%	4.912	1,032,400	18,400	1,077,100
7 5/8"	26.40	J-55	25.560	0.328	6.844	7.558	6.975	63.0%	64.9%	4.017	261,800	6,800	323,300

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
7 5/8"	26.40	L-80	25.560	0.328	6.844	7.558	6.975	63.0%	64.9%	4.017	380,800	9,900	424,000
7 5/8"	26.40	T-95	25.560	0.328	6.844	7.558	6.975	63.0%	64.9%	4.017	452,200	11,700	477,800
7 5/8"	26.40	P-110	25.560	0.328	6.844	7.558	6.975	63.0%	64.9%	4.017	523,600	13,600	564,500
7 5/8"	26.40	Q-125	25.560	0.328	6.844	7.558	6.975	63.0%	64.9%	4.017	595,100	15,500	618,300
7 5/8"	29.70	J-55	29.040	0.375	6.750	8.586	6.881	67.0%	69.0%	4.044	316,400	7,200	390,800
7 5/8"	29.70	L-80	29.040	0.375	6.750	8.586	6.881	67.0%	69.0%	4.044	460,300	10,500	512,400
7 5/8"	29.70	T-95	29.040	0.375	6.750	8.586	6.881	67.0%	69.0%	4.044	546,600	12,500	577,400
7 5/8"	29.70	P-110	29.040	0.375	6.750	8.586	6.881	67.0%	69.0%	4.044	632,900	14,500	682,200
7 5/8"	29.70	Q-125	29.040	0.375	6.750	8.586	6.881	67.0%	69.0%	4.044	719,200	16,500	747,200
7 5/8"	33.70	J-55	33.040	0.430	6.640	9.771	6.771	70.0%	72.0%	4.249	376,100	7,500	465,400
7 5/8"	33.70	L-80	33.040	0.430	6.640	9.771	6.771	70.0%	72.0%	4.249	547,100	11,000	608,400
7 5/8"	33.70	T-95	33.040	0.430	6.640	9.771	6.771	70.0%	72.0%	4.249	649,700	13,100	686,000
7 5/8"	33.70	P-110	33.040	0.430	6.640	9.771	6.771	70.0%	72.0%	4.249	752,300	15,100	810,300
7 5/8"	33.70	Q-125	33.040	0.430	6.640	9.771	6.771	70.0%	72.0%	4.249	854,900	17,200	887,900



# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
7 5/8"	39.00	J-55	38.050	0.500	6.500	11.252	6.631	73.0%	75.2%	5.047	451,700	7,900	557,300
7 5/8"	39.00	L-80	38.050	0.500	6.500	11.252	6.631	73.0%	75.2%	5.047	657,000	11,500	731,600
7 5/8"	39.00	T-95	38.050	0.500	6.500	11.252	6.631	73.0%	75.2%	5.047	780,200	13,600	824,400
7 5/8"	39.00	P-110	38.050	0.500	6.500	11.252	6.631	73.0%	75.2%	5.047	903,400	15,800	974,000
7 5/8"	39.00	Q-125	38.050	0.500	6.500	11.252	6.631	73.0%	75.2%	5.047	1,026,600	17,900	1,066,800
7 5/8"	42.80	J-55	42.390	0.562	6.376	12.528	6.507	75.0%	77.2%	5.204	516,900	8,100	638,600
7 5/8"	42.80	L-80	42.390	0.562	6.376	12.528	6.507	75.0%	77.2%	5.204	751,900	11,800	837,300
7 5/8"	42.80	T-95	42.390	0.562	6.376	12.528	6.507	75.0%	77.2%	5.204	892,900	14,000	943,500
7 5/8"	42.80	P-110	42.390	0.562	6.376	12.528	6.507	75.0%	77.2%	5.204	1,033,900	16,200	1,114,700
7 5/8"	42.80	Q-125	42.390	0.562	6.376	12.528	6.507	75.0%	77.2%	5.204	1,174,800	18,400	1,220,900
7 3/4"	46.10	J-55	45.470	0.595	6.500	13.447	6.579	75.0%	77.2%	5.393	554,500	8,100	684,000
7 3/4"	46.10	L-80	45.470	0.595	6.500	13.447	6.579	75.0%	77.2%	5.393	806,600	11,800	897,200
7 3/4"	46.10	T-95	45.470	0.595	6.500	13.447	6.579	75.0%	77.2%	5.393	957,900	14,000	1,011,300

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
7 3/4"	46.10	P-110	45.470	0.595	6.500	13.447	6.579	75.0%	77.2%	5.393	1,109,100	16,200	1,194,700
7 3/4"	46.10	Q-125	45.470	0.595	6.500	13.447	6.579	75.0%	77.2%	5.393	1,260,300	18,400	1,308,800
8 5/8"	44.00	J-55	43.390	0.500	7.500	12.830	7.635	72.0%	74.2%	5.08	508,300	7,800	618,400
8 5/8"	44.00	L-80	43.390	0.500	7.500	12.830	7.635	72.0%	74.2%	5.08	739,300	11,300	815,000
8 5/8"	44.00	T-95	43.390	0.500	7.500	12.830	7.635	72.0%	74.2%	5.08	878,000	13,400	920,900
8 5/8"	44.00	P-110	43.390	0.500	7.500	12.830	7.635	72.0%	74.2%	5.08	1,016,600	15,600	1,086,800
8 5/8"	44.00	Q-125	43.390	0.500	7.500	12.830	7.635	72.0%	74.2%	5.08	1,155,200	17,700	1,192,800
9 5/8"	40.00	J-55	38.940	0.395	8.679	11.513	8.842	69.0%	71.1%	4.555	437,000	7,400	523,200
9 5/8"	40.00	L-80	38.940	0.395	8.679	11.513	8.842	69.0%	71.1%	4.555	635,600	10,800	693,200
9 5/8"	40.00	T-95	38.940	0.395	8.679	11.513	8.842	69.0%	71.1%	4.555	754,800	12,900	785,700
9 5/8"	40.00	P-110	38.940	0.395	8.679	11.513	8.842	69.0%	71.1%	4.555	874,000	14,900	926,200
9 5/8"	40.00	Q-125	38.940	0.395	8.679	11.513	8.842	69.0%	71.1%	4.555	993,200	17,000	1,018,600

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
9 5/8"	43.50	J-55	42.690	0.435	8.625	12.625	8.768	70.0%	72.1%	4.457	486,000	7,500	582,000
9 5/8"	43.50	L-80	42.690	0.435	8.625	12.625	8.768	70.0%	72.1%	4.457	707,000	11,000	771,000
9 5/8"	43.50	T-95	42.690	0.435	8.625	12.625	8.768	70.0%	72.1%	4.457	839,500	13,100	873,900
9 5/8"	43.50	P-110	42.690	0.435	8.625	12.625	8.768	70.0%	72.1%	4.457	972,100	15,400	1,030,200
9 5/8"	43.50	Q-125	42.690	0.435	8.625	12.625	8.768	70.0%	72.1%	4.457	1,104,600	17,200	1,133,000
9 5/8"	47.00	J-55	46.140	0.472	8.525	13.644	8.688	72.0%	74.2%	4.897	540,500	7,800	647,300
9 5/8"	47.00	L-80	46.140	0.472	8.525	13.644	8.688	72.0%	74.2%	4.897	786,300	11,300	857,700
9 5/8"	47.00	T-95	46.140	0.472	8.525	13.644	8.688	72.0%	74.2%	4.897	933,700	13,400	971,900
9 5/8"	47.00	P-110	46.140	0.472	8.525	13.644	8.688	72.0%	74.2%	4.897	1,081,100	15,600	1,145,800
9 5/8"	47.00	Q-125	46.140	0.472	8.525	13.644	8.688	72.0%	74.2%	4.897	1,228,600	17,700	1,260,100
9 5/8"	53.50	J-55	52.850	0.545	8.500	15.629	8.567	74.0%	76.2%	4.951	636,200	8,000	762,000
9 5/8"	53.50	L-80	52.850	0.545	8.500	15.629	8.567	74.0%	76.2%	4.951	925,400	11,600	1,009,600
9 5/8"	53.50	T-95	52.850	0.545	8.500	15.629	8.567	74.0%	76.2%	4.951	1,098,900	13,800	1,144,000
9 5/8"	53.50	P-110	52.850	0.545	8.500	15.629	8.567	74.0%	76.2%	4.951	1,272,400	16,000	1,348,700

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
9 5/8"	53.50	Q-125	52.850	0.545	8.500	15.629	8.567	74.0%	76.2%	4.951	1,445,900	18,200	1,483,200
9 7/8"	62.80	J-55	61.740	0.625	8.500	18.259	8.640	77.0%	79.3%	5.804	772,800	8,300	922,100
9 7/8"	62.80	L-80	61.740	0.625	8.500	18.259	8.640	77.0%	79.3%	5.804	1,124,100	12,100	1,223,300
9 7/8"	62.80	T-95	61.740	0.625	8.500	18.259	8.640	77.0%	79.3%	5.804	1,334,900	14,400	1,387,200
9 7/8"	62.80	P-110	61.740	0.625	8.500	18.259	8.640	77.0%	79.3%	5.804	1,545,700	16,600	1,634,900
9 7/8"	62.80	Q-125	61.740	0.625	8.500	18.259	8.640	77.0%	79.3%	5.804	1,756,500	18,900	1,798,800
10 3/4"	40.50	J-55	38.880	0.350	9.894	11.494	10.062	64.0%	64.9%	45.38	404,600	6,900	475,900
10 3/4"	40.50	L-80	38.880	0.350	9.894	11.494	10.062	64.0%	64.9%	45.38	588,600	10,000	634,500
10 3/4"	40.50	T-95	38.880	0.350	9.894	11.494	10.062	64.0%	64.9%	45.38	698,900	11,900	721,400
10 3/4"	40.50	P-110	38.880	0.350	9.894	11.494	10.062	64.0%	64.9%	45.38	809,300	13,800	849,400
10 3/4"	40.50	Q-125	38.880	0.350	9.894	11.494	10.062	64.0%	64.9%	45.38	919,700	15,700	936,300
10 3/4"	45.50	J-55	44.220	0.400	9.875	13.074	9.978	64.0%	65.9%	4.772	460,200	6,900	541,600

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
10 3/4"	45.50	L-80	44.220	0.400	9.875	13.074	9.978	64.0%	65.9%	4.772	669,400	10,000	721,900
10 3/4"	45.50	T-95	44.220	0.400	9.875	13.074	9.978	64.0%	65.9%	4.772	795,000	11,900	820,700
10 3/4"	45.50	P-110	44.220	0.400	9.875	13.074	9.978	64.0%	65.9%	4.772	920,500	13,800	966,300
10 3/4"	45.50	Q-125	44.220	0.400	9.875	13.074	9.978	64.0%	65.9%	4.772	1,046,000	15,700	1,065,100
10 3/4"	51.00	J-55	49.500	0.450	9.694	14.637	9.862	67.0%	69.0%	4.765	539,400	7,200	634,900
10 3/4"	51.00	L-80	49.500	0.450	9.694	14.637	9.862	67.0%	69.0%	4.765	784,600	10,500	846,200
10 3/4"	51.00	T-95	49.500	0.450	9.694	14.637	9.862	67.0%	69.0%	4.765	93,180	12,500	962,000
10 3/4"	51.00	P-110	49.500	0.450	9.694	14.637	9.862	67.0%	69.0%	4.765	1,078,900	14,500	1,132,700
10 3/4"	51.00	Q-125	49.500	0.450	9.694	14.637	9.862	67.0%	69.0%	4.765	1,226,000	16,500	1,248,500
10 3/4"	55.50	J-55	54.210	0.495	9.604	16.031	9.772	70.0%	72.1%	4.901	617,500	7,500	726,700
10 3/4"	55.50	L-80	54.210	0.495	9.604	16.031	9.772	70.0%	72.1%	4.901	89,810	11,000	968,600
10 3/4"	55.50	T-95	54.210	0.495	9.604	16.031	9.772	70.0%	72.1%	4.901	1,066,600	13,100	1,101,200
10 3/4"	55.50	P-110	54.210	0.495	9.604	16.031	9.772	70.0%	72.1%	4.901	1,235,000	15,100	1,296,500
10 3/4"	55.50	Q-125	54.210	0.495	9.604	16.031	9.772	70.0%	72.1%	4.901	1,403,400	17,200	1,429,100

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
10 3/4"	60.70	J-55	59.400	0.545	9.504	17.565	9.672	73.0%	75.2%	5.549	705,000	79,000	829,600
10 3/4"	60.70	L-80	59.400	0.545	9.504	17.565	9.672	73.0%	75.3%	5.549	1,025,400	11,500	1,105,800
10 3/4"	60.70	T-95	59.400	0.545	9.504	17.565	9.672	73.0%	75.4%	5.549	1,217,700	13,600	1,257,200
10 3/4"	60.70	P-110	59.400	0.545	9.504	17.565	9.672	73.0%	75.5%	5.549	1,410,000	15,800	1,480,200
10 3/4"	60.70	Q-125	59.400	0.545	9.504	17.565	9.672	73.0%	75.6%	5.549	1,602,300	17,900	1,631,600
10 3/4"	65.70	J-55	64.530	0.595	9.500	19.083	9.591	73.0%	75.2%	5.297	766,300	7,900	902,200
10 3/4"	65.70	L-80	64.530	0.595	9.500	19.083	9.591	73.0%	75.2%	5.297	1,114,600	11,500	1,202,300
10 3/4"	65.70	T-95	64.530	0.595	9.500	19.083	9.591	73.0%	75.2%	5.297	1,323,700	13,600	1,366,800
10 3/4"	65.70	P-110	64.530	0.595	9.500	19.083	9.591	73.0%	75.2%	5.297	1,532,700	15,800	1,609,300
10 3/4"	65.70	Q-125	64.530	0.595	9.500	19.083	9.591	73.0%	75.2%	5.297	1,741,700	17,900	1,773,800
11 3/4"	47.00	J-55	45.600	0.375	10.844	13.470	11.016	0.7%	67.0%	4.846	481,700	7,000	557,600
11 3/4"	47.00	L-80	45.600	0.375	10.844	13.470	11.016	0.7%	67.0%	4.846	700,700	10,200	747,500
11 3/4"	47.00	T-95	45.600	0.375	10.844	13.470	11.016	0.7%	67.0%	4.846	832,100	12,100	852,400

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
11 3/4"	47.00	P-110	45.600	0.375	10.844	13.470	11.016	0.7%	67.0%	4.846	963,400	14,000	1,002,400
11 3/4"	47.00	Q-125	45.600	0.375	10.844	13.470	11.016	0.7%	67.0%	4.846	1,094,800	16,000	1,107,300
11 3/4"	54.00	J-55	52.620	0.435	10.724	15.543	10.896	68.0%	70.0%	4.832	581,200	7,300	672,900
11 3/4"	54.00	L-80	52.620	0.435	10.724	15.543	10.896	68.0%	70.0%	4.832	845,400	10,700	902,000
11 3/4"	54.00	T-95	52.620	0.435	10.724	15.543	10.896	68.0%	70.0%	4.832	1,004,000	12,700	1,028,600
11 3/4"	54.00	P-110	52.620	0.435	10.724	15.543	10.896	68.0%	70.0%	4.832	1,162,500	14,700	1,209,600
11 3/4"	54.00	Q-125	52.620	0.435	10.724	15.543	10.896	68.0%	70.0%	4.832	1,321,000	16,700	1,336,200
11 3/4"	60.00	J-55	58.810	0.489	10.625	17.390	10.790	70.0%	72.1%	4.877	669,300	7,500	775,100
11 3/4"	60.00	L-80	58.810	0.489	10.625	17.390	10.790	70.0%	72.1%	4.877	973,600	11,000	1,038,900
11 3/4"	60.00	T-95	58.810	0.489	10.625	17.390	10.790	70.0%	72.1%	4.877	1,156,200	13,100	1,184,700
11 3/4"	60.00	P-110	58.810	0.489	10.625	17.390	10.790	70.0%	72.1%	4.877	1,338,700	15,100	1,393,200
11 3/4"	60.00	Q-125	58.810	0.489	10.625	17.390	10.790	70.0%	72.1%	4.877	1,521,300	17,200	1,538,900
11 3/4"	65.00	J-55	63.970	0.534	10.625	18.915	10.718	72.0%	74.1%	5.396	748,800	7,800	867,200
11 3/4"	65.00	L-80	63.970	0.534	10.625	18.915	10.718	72.0%	74.1%	5.396	1,089,200	11,300	1,162,300

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
11 3/4"	65.00	T-95	63.970	0.534	10.625	18.915	10.718	72.0%	74.1%	5.396	1,293,400	13,400	1,325,300
11 3/4"	65.00	P-110	63.970	0.534	10.625	18.915	10.718	72.0%	74.1%	5.396	1,497,600	15,600	1,558,600
11 3/4"	65.00	Q-125	63.970	0.534	10.625	18.915	10.718	72.0%	74.1%	5.396	1,701,800	17,700	1,721,600
11 7/8"	71.80	J-55	70.190	0.582	10.625	20.757	10.741	75.0%	77.2%	6.065	856,100	8,100	989,300
11 7/8"	71.80	L-80	70.190	0.582	10.625	20.757	10.741	75.0%	77.2%	6.065	4,245,300	11,800	1,327,000
11 7/8"	71.80	T-95	70.190	0.582	10.625	20.757	10.741	75.0%	77.2%	6.065	1,478,800	14,000	1,513,700
11 7/8"	71.80	P-110	70.190	0.582	10.625	20.757	10.741	75.0%	77.2%	6.065	1,712,300	16,200	1,779,900
11 7/8"	71.80	Q-125	70.190	0.582	10.625	20.757	10.741	75.0%	77.2%	6.065	1,945,800	18,400	1,966,600
13 3/8"	54.50	J-55	52.740	0.380	12.459	15.593	12.637	67.0%	69.0%	4.2925	574,800	7,200	647,600
13 3/8"	54.50	L-80	52.740	0.380	12.459	15.593	12.637	67.0%	69.0%	4.2925	836,100	10,500	876,100
13 3/8"	54.50	T-95	52.740	0.380	12.459	15.593	12.637	67.0%	69.0%	4.2925	992,900	12,500	1,004,500
13 3/8"	54.50	P-110	52.740	0.380	12.459	15.593	12.637	67.0%	69.0%	4.2925	1,159,700	14,500	1,179,000



# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
13 3/8"	54.50	Q-125	52.740	0.380	12.459	15.593	12.637	67.0%	69.0%	4.2925	1,306,500	16,500	1,307,000
13 3/8"	61.00	J-55	59.500	0.430	12.359	17.578	12.537	68.0%	70.0%	4.664	657,300	7,300	740,600
13 3/8"	61.00	L-80	59.500	0.430	12.359	17.578	12.537	68.0%	70.0%	4.664	956,100	10,700	1,002,500
13 3/8"	61.00	T-95	59.500	0.430	12.359	17.578	12.537	68.0%	70.0%	4.664	1,135,400	12,700	1,148,800
13 3/8"	61.00	P-110	59.500	0.430	12.359	17.578	12.537	68.0%	70.0%	4.664	1,314,600	14,700	1,348,400
13 3/8"	61.00	Q-125	59.500	0.430	12.359	17.578	12.537	68.0%	70.0%	4.664	1,493,900	16,700	1,494,800
13 3/8"	68.00	J-55	66.100	0.480	12.259	19.546	12.437	78.0%	70.0%	5.168	730,500	7,300	823,700
13 3/8"	68.00	L-80	66.100	0.480	12.259	19.546	12.437	78.0%	70.0%	5.168	1,062,500	10,700	1,114,400
13 3/8"	68.00	T-95	66.100	0.480	12.259	19.546	12.437	78.0%	70.0%	5.168	1,261,800	12,700	1,277,000
13 3/8"	68.00	P-110	66.100	0.480	12.259	19.546	12.437	78.0%	70.0%	5.168	1,461,000	14,700	1,499,000
13 3/8"	68.00	Q-125	66.100	0.480	12.259	19.546	12.437	78.0%	70.0%	5.168	1,660,200	16,700	1,661,500
13 3/8"	72.00	J-55	70.600	0.514	12.250	20.876	12.381	68.0%	70.1%	4.464	781,200	7,300	881,200
13 3/8"	72.00	L-80	70.600	0.514	12.250	20.876	12.381	68.0%	70.1%	4.464	1,136,300	10,700	1,192,100
13 3/8"	72.00	T-95	70.600	0.514	12.250	20.876	12.381	68.0%	70.1%	4.464	1,349,400	12,700	1,365,900

# ULT-FJ SUMMARY

[www.tarponpipe.com](http://www.tarponpipe.com)



PIPE BODY							CONNECTION						
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	DRIFT DIAMETER	AVERAGE PBA	BORED I.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	MAKE-UP LOSS	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	in.	?	in.	%	%	in.	ft./lbs.	ft.	ft./lbs.
13 3/8"	72.00	P-110	70.600	0.514	12.250	20.876	12.381	68.0%	70.1%	4.464	1,562,500	14,700	1,603,300
13 3/8"	72.00	Q-125	70.600	0.514	12.250	20.876	12.381	68.0%	70.1%	4.464	1,775,500	16,700	1,771,000
13 5/8"	88.20	J-55	86.780	6.250	12.250	25.659	12.405	74.0%	76.2%	5.646	1,044,400	8,000	
13 5/8"	88.20	L-80	86.780	6.250	12.250	25.659	12.405	74.0%	76.2%	5.646	1,519,100	11,600	1,589,300
13 5/8"	88.20	T-95	86.780	6.250	12.250	25.659	12.405	74.0%	76.2%	5.646	1,804,000	13,800	1,822,400
13 5/8"	88.20	P-110	86.780	6.250	12.250	25.659	12.405	74.0%	76.2%	5.646	2,088,800	16,000	2,138,600
13 5/8"	88.20	Q-125	86.780	6.250	12.250	25.659	12.405	74.0%	76.2%	5.646	2,373,700	18,200	2,371,700