

ULT FS Summary



FS SUMMARY

www.tarponpipe.com

PIPE BODY								CONNECTION							
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	NOMINAL I.D.	DRIFT DIAMETER	AREA	TURNED O.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	BORED I.D.	THREAD LENGTH	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	?	in.	sq. in.	in.	%	%	?	in.	ft./lbs.	ft.	ft./lbs.
4"	11.60	L-80	11.340	0.286	3.428	3.303	3.350	4.149	90.1%	0.9%	0.034	0.055	245,600	14,140	278,300
4"	11.60	T-95	11.340	0.286	3.428	3.303	3.350	4.149	90.1%	0.9%	1.034	1.055	285,700	16,790	310,700
4"	11.60	P-110	11.340	0.286	3.428	3.303	3.350	4.149	90.1%	0.9%	2.034	2.055	330,800	19,440	368,400
4"	11.60	Q-125	11.340	0.286	3.428	3.303	3.350	4.149	90.1%	0.9%	3.034	3.055	375,900	22,090	400,800
4"	13.20	L-80	12.930	0.330	3.340	3.215	3.820	4.146	91.0%	92.5%	3.296	5.215	277,000	14,280	320,400
4"	13.20	T-95	12.930	0.330	3.340	3.215	3.820	4.146	91.0%	92.5%	3.296	5.215	328,900	16,950	357,600
4"	13.20	P-110	12.930	0.330	3.340	3.215	3.820	4.146	91.0%	92.5%	3.296	5.215	380,900	19,630	424,200
4"	13.20	Q-125	12.930	0.330	3.340	3.215	3.820	4.146	91.0%	92.5%	3.296	5.215	432,800	22,310	461,600
4"	14.68	L-80	14.680	0.380	3.240	3.115	4.339	4.146	92.3%	93.7%	3.196	6.021	318,900	14,480	368,900
4"	14.68	T-95	14.680	0.380	3.240	3.115	4.339	4.146	92.3%	93.7%	3.196	6.021	378,700	17,190	411,900
4"	14.68	P-110	14.680	0.380	3.240	3.115	4.339	4.146	92.3%	93.7%	3.196	6.021	438,500	19,910	488,400
4"	14.68	Q-125	14.680	0.380	3.240	3.115	4.339	4.146	92.3%	93.7%	3.196	6.021	498,300	22,620	531,400
4 1/2"	12.60	L-80	12.240	0.271	3.958	3.833	3.615	4.654	90.5%	92.0%	3.914	5.197	260,500	14,180	299,800
4 1/2"	12.60	T-95	12.240	0.271	3.958	3.833	3.615	5.654	90.5%	92.0%	3.914	5.197	309,400	16,850	335,200
4 1/2"	12.60	P-110	12.240	0.271	3.958	3.833	3.615	6.654	90.5%	92.0%	3.914	5.197	358,200	19,500	397,300
4 1/2"	12.60	Q-125	12.240	0.271	3.958	3.833	3.615	7.654	90.5%	92.0%	3.914	5.197	407,100	22,170	432,700
4 1/2"	13.50	L-80	13.010	0.290	3.920	3.795	3.851	4.648	90.0%	91.5%	3.876	5.480	276,000	14,110	317,700

ULT FS Summary



FS SUMMARY

www.tarponpipe.com

PIPE BODY								CONNECTION							
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	NOMINAL I.D.	DRIFT DIAMETER	AREA	TURNED O.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	BORED I.D.	THREAD LENGTH	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	?	in.	sq. in.	in.	%	%	?	in.	ft./lbs.	ft.	ft./lbs.
4 1/2"	13.50	T-95	13.010	0.290	3.920	3.795	3.851	5.648	90.0%	91.5%	3.876	5.480	327,700	16,750	355,100
4 1/2"	13.50	P-110	13.010	0.290	3.920	3.795	3.851	6.648	90.0%	91.5%	3.876	5.480	379,500	19,400	420,900
4 1/2"	13.50	Q-125	13.010	0.290	3.920	3.795	3.851	7.648	90.0%	91.5%	3.876	5.480	431,200	22,040	458,300
4 1/2"	15.10	L-80	14.980	0.337	0.383	3.701	4.425	4.656	92.7%	94.2%	3.782	5.423	326,700	14,530	376,100
4 1/2"	15.10	T-95	14.980	0.337	0.383	3.701	4.425	5.656	92.7%	94.2%	3.782	5.423	388,000	17,260	420,500
4 1/2"	15.10	P-110	14.980	0.337	0.383	3.701	4.425	6.656	92.7%	94.2%	3.782	5.423	449,300	19,990	498,300
4 1/2"	15.10	Q-125	14.980	0.337	0.383	3.701	4.425	7.656	92.7%	94.2%	3.782	5.423	510,600	22,720	542,700
4 1/2"	17.00	L-80	16.720	0.380	3.740	3.615	4.939	4.663	94.6%	96.1%	3.698	6.206	372,100	14,830	428,300
4 1/2"	17.00	T-95	16.720	0.380	3.740	3.615	4.939	5.663	94.6%	96.1%	3.698	6.206	441,900	17,610	478,800
4 1/2"	17.00	P-110	16.720	0.380	3.740	3.615	4.939	6.663	94.6%	96.1%	3.698	6.206	511,700	20,400	567,500
4 1/2"	17.00	Q-125	16.720	0.380	3.740	3.615	4.939	7.663	94.6%	96.1%	3.698	6.206	581,400	23,180	618,000
4 1/2"	18.80	L-80	18.690	0.430	3.640	3.515	5.521	4.667	89.6%	91.0%	3.596	5.308	393,900	14,050	453,600
4 1/2"	18.80	T-95	18.690	0.430	3.640	3.516	6.521	5.667	89.6%	91.0%	3.596	5.308	467,800	16,680	507,100
4 1/2"	18.80	P-110	18.690	0.430	3.640	3.517	7.521	6.667	89.6%	91.0%	3.596	5.308	541,700	19,320	601,000
4 1/2"	18.80	Q-125	18.690	0.430	3.640	3.518	8.521	7.667	89.6%	91.0%	3.596	5.308	615,600	21,950	654,500
5"	15.00	L-80	14.870	0.296	4.408	4.283	4.392	5.153	90.2%	91.8%	4.364	5.599	315,700	14,150	361,600
5"	15.00	T-95	14.870	0.296	4.408	4.283	4.392	6.153	90.2%	91.8%	4.364	5.599	374,900	16,800	404,800

ULT FS Summary



FS SUMMARY

www.tarponpipe.com

PIPE BODY								CONNECTION							
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	NOMINAL I.D.	DRIFT DIAMETER	AREA	TURNED O.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	BORED I.D.	THREAD LENGTH	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	?	in.	sq. in.	in.	%	%	?	in.	ft./lbs.	ft.	ft./lbs.
5"	15.00	P-110	14.870	0.296	4.408	4.283	4.392	7.153	90.2%	91.8%	4.364	5.599	434,100	19,460	479,500
5"	15.00	Q-125	14.870	0.296	4.408	4.283	4.392	8.153	90.2%	91.8%	4.364	5.599	493,300	22,110	522,600
5"	18.00	L-80	17.930	0.362	4.276	4.151	5.296	5.165	93.8%	95.3%	4.232	5.862	395,800	14,710	453,300
5"	18.00	T-95	17.930	0.362	4.276	4.151	5.296	6.165	93.8%	95.3%	4.232	5.862	470,000	17,471	507,500
5"	18.00	P-110	17.930	0.362	4.276	4.151	5.296	7.165	93.8%	95.3%	4.232	5.862	544,200	20,230	601,100
5"	18.00	Q-125	17.930	0.362	4.276	4.151	5.296	8.165	93.8%	95.3%	4.232	5.862	618,500	22,990	655,300
5"	20.30	L-80	20.010	0.408	4.184	4.059	5.910	5.187	91.2%	92.6%	4.140	5.206	429,200	14,290	491,700
5"	20.30	T-95	20.010	0.408	4.184	4.059	5.910	6.187	91.2%	92.6%	4.140	5.206	509,700	16,980	550,400
5"	20.30	P-110	20.010	0.408	4.184	4.059	5.910	7.187	91.2%	92.6%	4.140	5.206	590,100	19,660	651,900
5"	20.30	Q-125	20.010	0.408	4.184	4.059	5.910	8.187	91.2%	92.6%	4.140	5.206	670,600	22,340	710,600
5"	21.40	L-80	21.300	0.437	4.126	4.001	6.290	5.188	91.6%	93.0%	4.112	5.390	444,500	14,360	509,200
5"	21.40	T-95	21.300	0.437	4.126	4.001	6.290	6.188	91.6%	93.0%	4.112	5.390	527,800	17,050	570,000
5"	21.40	P-110	21.300	0.437	4.126	4.001	6.290	7.188	91.6%	93.0%	4.112	5.390	611,200	19,750	675,200
5"	21.40	Q-125	21.300	0.437	4.126	4.001	6.290	8.188	91.6%	93.0%	4.112	5.390	694,500	22,440	736,000
5"	23.20	L-80	23.080	0.478	4.044	3.919	6.619	5.189	91.8%	93.0%	4.082	5.580	460,100	14,400	527,100
5"	23.20	T-95	23.080	0.478	4.044	3.919	6.619	6.189	91.8%	93.0%	4.082	5.580	546,400	17,100	590,000
5"	23.20	P-110	23.080	0.478	4.044	3.919	6.619	7.189	91.8%	93.0%	4.082	5.580	632,600	19,790	698,900
5"	23.20	Q-125	23.080	0.478	4.044	3.919	6.619	8.189	91.8%	93.0%	4.082	5.580	718,900	22,500	761,800

ULT FS Summary



FS SUMMARY

www.tarponpipe.com

PIPE BODY								CONNECTION							
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	NOMINAL I.D.	DRIFT DIAMETER	AREA	TURNED O.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	BORED I.D.	THREAD LENGTH	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	?	in.	sq. in.	in.	%	%	?	in.	ft./lbs.	ft.	ft./lbs.
5"	24.10	L-80	24.300	0.500	4.000	3.875	7.098	5.189	92.6%	94.0%	4.000	6.960	502,800	14,520	576,000
5"	24.10	T-95	24.300	0.500	4.000	3.875	7.098	5.189	92.6%	94.0%	4.000	6.960	597,100	17,240	644,800
5"	24.10	P-110	24.300	0.500	4.000	3.875	7.098	5.189	92.6%	94.0%	4.000	6.960	691,400	19,970	763,800
5"	24.10	Q-125	24.300	0.500	4.000	3.875	7.098	5.189	92.6%	94.0%	4.000	6.960	785,600	22,690	832,600
5 1/2"	17.00	L-80	16.870	0.304	4.892	4.767	4.982	5.187	92.9%	94.2%	3.956	6.371	525,000	14,560	601,500
5 1/2"	17.00	T-95	16.870	0.304	4.892	4.767	4.982	5.187	92.9%	94.2%	3.956	6.371	623,500	17,290	673,300
5 1/2"	17.00	P-110	16.870	0.304	4.892	4.767	4.982	5.187	92.9%	94.2%	3.956	6.371	721,900	20,020	797,600
5 1/2"	17.00	Q-125	16.870	0.304	4.892	4.767	4.982	5.187	92.9%	94.2%	3.956	6.371	820,400	22,760	869,400
5 1/2"	20.00	L-80	19.810	0.361	4.778	4.653	5.852	5.658	91.2%	92.8%	4.848	5.864	362,100	14,300	412,700
5 1/2"	20.00	T-95	19.810	0.361	4.778	4.653	5.852	5.658	91.2%	92.8%	4.848	5.864	430,000	16,990	162,600
5 1/2"	20.00	P-110	19.810	0.361	4.778	4.653	5.852	5.658	91.2%	92.8%	4.848	5.864	497,900	19,670	547,700
5 1/2"	20.00	Q-125	19.810	0.361	4.778	4.653	5.852	5.658	91.2%	92.8%	4.848	5.864	565,800	22,350	597,600
5 1/2"	23.00	L-80	22.540	0.415	4.670	4.545	8.657	5.648	91.1%	92.6%	4.734	5.577	424,500	14,280	483,900
5 1/2"	23.00	T-95	22.540	0.415	4.670	4.545	8.657	5.648	91.1%	92.6%	4.734	5.577	504,200	16,960	542,400
5 1/2"	23.00	P-110	22.540	0.415	4.670	4.545	8.657	5.648	91.1%	92.6%	4.734	5.577	583,800	19,640	642,100
5 1/2"	23.00	Q-125	22.540	0.415	4.670	4.545	8.657	5.648	91.1%	92.6%	4.734	5.577	663,400	22,320	700,700
5 1/2"	26.00	L-80	25.540	0.476	4.548	4.423	7.544	5.713	94.8%	96.2%	4.504	5.526	496,200	14,670	565,500

ULT FS Summary



FS SUMMARY

www.tarponpipe.com

PIPE BODY								CONNECTION							
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	NOMINAL I.D.	DRIFT DIAMETER	AREA	TURNED O.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	BORED I.D.	THREAD LENGTH	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	?	in.	sq. in.	in.	%	%	?	in.	ft./lbs.	ft.	ft./lbs.
5 1/2"	26.00	T-95	25.540	0.476	4.548	4.423	7.544	5.713	94.8%	96.2%	4.504	5.526	489,200	17,420	633,900
5 1/2"	26.00	P-110	25.540	0.476	4.548	4.423	7.544	5.713	94.8%	96.2%	4.504	5.526	682,300	20,180	750,500
5 1/2"	26.00	Q-125	25.540	0.476	4.548	4.423	7.544	5.713	94.8%	96.2%	4.504	5.526	775,300	22,930	816,900
5 1/2"	26.80	L-80	26.700	0.500	4.500	4.375	7.886	5.708	94.8%	96.2%	4.504	6.294	569,600	14,860	649,100
5 1/2"	26.80	T-95	26.700	0.500	4.500	4.375	7.886	5.708	94.8%	96.2%	4.504	6.294	676,400	17,650	727,700
5 1/2"	26.80	P-110	26.700	0.500	4.500	4.375	7.886	5.708	94.8%	96.2%	4.504	6.294	783,200	20,440	861,500
5 1/2"	26.80	Q-125	26.700	0.500	4.500	4.375	7.886	5.708	94.8%	96.2%	4.504	6.294	890,000	23,230	940,000
5 1/2"	29.70	L-80	29.640	0.562	4.376	4.251	8.755	5.689	92.8%	94.2%	4.456	6.368	583,200	14,560	664,800
5 1/2"	29.70	T-95	29.640	0.562	4.376	4.251	8.755	5.689	92.8%	94.2%	4.456	6.368	692,600	17,290	745,200
5 1/2"	29.70	P-110	29.640	0.562	4.376	4.251	8.755	5.689	92.8%	94.2%	4.456	6.368	801,900	20,020	882,200
5 1/2"	29.70	Q-125	29.640	0.562	4.376	4.251	8.755	5.689	92.8%	94.2%	4.456	6.368	911,300	22,750	962,600
6 5/8"	20.00	L-80	19.490	0.288	6.149	5.924	5.756	5.709	87.9%	89.2%	4.332	5.973	613,000	13,780	699,200
6 5/8"	20.00	T-95	19.490	0.288	6.149	5.924	5.756	5.709	87.9%	89.2%	4.332	5.973	727,900	16,370	783,600
6 5/8"	20.00	P-110	19.490	0.288	6.149	5.924	5.756	5.709	87.9%	89.2%	4.332	5.973	842,900	18,950	927,800
6 5/8"	20.00	Q-125	19.490	0.288	6.149	5.924	5.756	5.709	87.9%	89.2%	4.332	5.973	957,800	24,540	1,012,200
6 5/8"	24.00	L-80	23.580	0.352	5.921	5.796	6.964	6.797	92.4%	93.9%	6.005	5.559	423,600	14,480	477,200
6 5/8"	24.00	T-95	23.580	0.352	5.921	5.796	6.964	6.797	92.4%	93.9%	6.005	5.559	503,000	17,200	536,600

ULT FS Summary



FS SUMMARY

www.tarponpipe.com

PIPE BODY								CONNECTION							
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	NOMINAL I.D.	DRIFT DIAMETER	AREA	TURNED O.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	BORED I.D.	THREAD LENGTH	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	?	in.	sq. in.	in.	%	%	?	in.	ft./lbs.	ft.	ft./lbs.
6 5/8"	24.00	P-110	23.580	0.352	5.921	5.796	6.964	6.797	92.4%	93.9%	6.005	5.559	582,500	19,920	634,500
6 5/8"	24.00	Q-125	23.580	0.352	5.921	5.796	6.964	6.797	92.4%	93.9%	6.005	5.559	661,900	22,640	693,900
6 5/8"	24.60	L-80	24.210	0.362	5.904	5.776	7.151	6.789	92.6%	94.1%	5.877	5.573	513,600	14,520	578,600
6 5/8"	24.60	T-95	24.210	0.362	5.904	5.776	7.151	6.789	92.6%	94.1%	5.877	5.573	609,900	17,240	650,600
6 5/8"	24.60	P-110	24.210	0.362	5.904	5.776	7.151	6.789	92.6%	94.1%	5.877	5.573	706,200	19,960	769,400
6 5/8"	24.60	Q-125	24.210	0.362	5.904	5.776	7.151	6.789	92.6%	94.1%	5.877	5.573	802,500	22,680	841,400
6 5/8"	28.00	L-80	27.650	0.417	5.791	5.666	8.165	6.781	91.6%	93.1%	5.857	5.609	521,800	14,360	588,000
6 5/8"	28.00	T-95	27.650	0.417	5.791	5.666	8.165	6.781	91.6%	93.1%	5.857	5.609	619,700	17,060	661,100
6 5/8"	28.00	P-110	27.650	0.417	5.791	5.666	8.165	6.781	91.6%	93.1%	5.857	5.609	717,500	19,750	781,800
6 5/8"	28.00	Q-125	27.650	0.417	5.791	5.666	8.165	6.781	91.6%	93.1%	5.857	5.609	815,400	22,450	854,900
6 5/8"	32.00	L-80	31.200	0.475	5.675	5.550	9.214	6.839	93.9%	95.4%	5.747	5.528	610,900	14,720	688,300
6 5/8"	32.00	T-95	31.200	0.475	5.675	5.550	9.214	6.839	93.9%	95.4%	5.747	5.528	725,400	17,490	773,900
6 5/8"	32.00	P-110	31.200	0.475	5.675	5.550	9.214	6.839	93.9%	95.4%	5.747	5.528	840,000	20,250	915,200
6 5/8"	32.00	Q-125	31.200	0.475	5.675	5.550	9.214	6.839	93.9%	95.4%	5.747	5.528	954,500	23,010	1,000,800
6 5/8"	33.00	L-80	32.710	0.500	5.625	5.500	9.660	6.849	95.8%	97.3%	5.631	6.374	703,600	15,030	792,700
6 5/8"	33.00	T-95	32.710	0.500	5.625	5.500	9.660	6.849	95.8%	97.3%	5.631	6.374	835,500	17,850	891,300
6 5/8"	33.00	P-110	32.710	0.500	5.625	5.500	9.660	6.849	95.8%	97.3%	5.631	6.374	967,400	20,670	1,053,900
6 5/8"	33.00	Q-125	32.710	0.500	5.625	5.500	9.660	6.849	95.8%	97.3%	5.631	6.374	1,099,300	23,480	1,152,600

ULT FS Summary



FS SUMMARY

www.tarponpipe.com

PIPE BODY								CONNECTION							
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	NOMINAL I.D.	DRIFT DIAMETER	AREA	TURNED O.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	BORED I.D.	THREAD LENGTH	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	?	in.	sq. in.	in.	%	%	?	in.	ft./lbs.	ft.	ft./lbs.
6 5/8"	34.50	L-80	34.200	5.250	5.275	5.450	10.102	6.817	92.5%	93.9%	5.581	6.310	711,800	14,500	802,200
6 5/8"	34.50	T-95	34.200	5.250	5.275	5.450	10.102	6.817	92.5%	93.9%	5.581	6.310	845,300	17,220	902,000
6 5/8"	34.50	P-110	34.200	5.250	5.275	5.450	10.102	6.817	92.5%	93.9%	5.581	6.310	978,800	19,940	1,066,600
6 5/8"	34.50	Q-125	34.200	5.250	5.275	5.450	10.102	6.817	92.5%	93.9%	5.581	6.310	1,112,200	23,660	1,166,400
6 5/8"	36.70	L-80	36.390	0.562	5.501	5.376	10.749	6.881	91.3%	92.6%	5.531	5.951	734,700	14,320	828,100
6 5/8"	36.70	T-95	36.390	0.562	5.501	5.376	10.749	6.881	91.3%	92.6%	5.531	5.951	872,400	17,000	931,100
6 5/8"	36.70	P-110	36.390	0.562	5.501	5.376	10.749	6.881	91.3%	92.6%	5.531	5.951	1,010,200	19,690	1,101,000
7 5/8"	37.70	Q-225	36.390	0.562	5.501	5.376	10.749	6.881	91.3%	92.6%	6.531	6.951	1,147,900	22,370	1,204,000
7"	23.00	L-80	22.630	0.317	6.386	6.241	6.682	6.881	91.9%	93.2%	5.457	6.404	787,000	14,410	887,100
7"	23.00	T-95	22.630	0.317	6.386	6.241	6.682	6.881	91.9%	93.2%	5.457	6.404	934,600	17,120	997,400
7"	23.00	P-110	22.630	0.317	6.386	6.241	6.682	6.881	91.9%	93.2%	5.457	6.404	1,082,100	19,820	1,179,400
7"	23.00	Q-125	22.630	0.317	6.386	6.241	6.682	6.881	91.9%	93.2%	5.457	6.404	1,229,700	22,520	1,289,700
7"	26.00	L-80	25.660	0.362	6.276	6.151	7.579	7.169	92.5%	94.1%	6.322	5.103	492,700	14,510	553,000
7"	26.00	T-95	25.660	0.362	6.276	6.151	7.579	7.169	92.5%	94.1%	6.322	5.103	585,100	17,230	622,500
7"	26.00	P-110	25.660	0.362	6.276	6.151	7.579	7.169	92.5%	94.1%	6.322	5.103	677,500	19,950	735,700
7"	26.00	Q-125	25.660	0.362	6.276	6.151	7.579	7.169	92.5%	94.1%	6.322	5.103	769,900	22,680	8,052,000
7"	29.00	L-80	28.720	0.408	6.184	6.059	8.483	7.158	91.8%	93.3%	6.232	5.634	554,600	14,400	622,500

ULT FS Summary



FS SUMMARY

www.tarponpipe.com

PIPE BODY								CONNECTION							
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	NOMINAL I.D.	DRIFT DIAMETER	AREA	TURNED O.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	BORED I.D.	THREAD LENGTH	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	?	in.	sq. in.	in.	%	%	?	in.	ft./lbs.	ft.	ft./lbs.
7"	29.00	T-95	28.720	0.408	6.184	6.059	8.483	7.158	91.8%	93.3%	6.232	5.634	658,600	17,110	700,700
7"	29.00	P-110	28.720	0.408	6.184	6.059	8.483	7.158	91.8%	93.3%	6.232	5.634	762,600	19,810	828,200
7"	29.00	Q-125	28.720	0.408	6.184	6.059	8.483	7.158	91.8%	93.3%	6.232	5.634	866,600	22,510	903,400
7"	32.00	L-80	31.670	0.453	6.940	6.000	9.355	7.215	93.7%	98.8%	6.061	6.109	633,600	14,700	711,200
7"	32.00	T-95	31.670	0.453	6.940	6.000	9.355	7.215	93.7%	98.8%	6.061	6.109	752,400	17,480	800,500
7"	32.00	P-110	31.670	0.453	6.940	6.000	9.355	7.215	93.7%	98.8%	6.061	6.109	871,200	20,220	946,200
7"	32.00	Q-125	31.670	0.453	6.940	6.000	9.355	7.215	93.7%	98.8%	6.061	6.109	990,100	22,980	1,035,500
7"	35.00	L-80	34.580	0.453	6.004	5.879	10.214	7.248	93.0%	94.4%	5.960	6.342	724,900	15,250	813,500
7"	35.00	T-95	34.580	0.453	6.004	5.879	10.214	7.248	93.0%	94.4%	5.960	6.342	860,900	18,120	915,700
7"	35.00	P-110	34.580	0.453	6.004	5.879	10.214	7.248	93.0%	94.4%	5.960	6.342	996,800	20,980	1,082,300
7"	35.00	Q-125	34.580	0.453	6.004	5.879	10.214	7.248	93.0%	94.4%	5.960	6.342	1,132,700	23,840	1,184,600
7"	38.00	L-80	37.260	0.540	5.920	5.795	11.004	7.197	93.3%	94.6%	5.876	6.268	756,600	14,580	849,400
7"	38.00	T-95	37.260	0.540	5.920	5.795	11.004	7.197	93.3%	94.6%	5.876	6.268	898,500	17,320	956,100
7"	38.00	P-110	37.260	0.540	5.920	5.795	11.004	7.197	93.3%	94.6%	5.876	6.268	1,040,400	20,050	1,130,100
7"	38.00	Q-125	37.260	0.540	5.920	5.795	11.004	7.197	93.3%	94.6%	5.876	6.268	1,182,300	22,790	1,236,800
7"	41.00	L-80	40.390	0.590	5.820	5.695	11.930	7.274	95.1%	96.4%	5.776	6.261	817,800	14,630	918,200
7"	41.00	T-95	40.390	0.590	5.820	5.695	11.930	7.274	95.1%	96.4%	5.776	6.261	971,200	17,370	1,033,500
7"	41.00	P-110	40.390	0.590	5.820	5.695	11.930	7.274	95.1%	96.4%	5.776	6.261	1,124,500	20,110	1,221,600

ULT FS Summary



FS SUMMARY

www.tarponpipe.com

PIPE BODY								CONNECTION							
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	NOMINAL I.D.	DRIFT DIAMETER	AREA	TURNED O.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	BORED I.D.	THREAD LENGTH	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	?	in.	sq. in.	in.	%	%	?	in.	ft./lbs.	ft.	ft./lbs.
7"	41.00	Q-125	40.390	0.590	5.820	5.695	11.930	7.274	95.1%	96.4%	5.776	6.261	1,277,900	22,860	1,336,800
7"	42.70	L-80	42.550	0.625	5.750	5.625	12.569	7.287	95.1%	96.4%	5.776	6.261	903,800	14,910	1,014,600
7"	42.70	T-95	42.550	0.625	5.750	5.625	12.569	7.287	95.1%	96.4%	5.776	6.261	1,073,300	17,710	1,142,000
7"	42.70	P-110	42.550	0.625	5.750	5.625	12.569	7.287	95.1%	96.4%	5.776	6.261	1,242,700	20,510	1,349,900
7"	42.70	Q-125	42.550	0.625	5.750	5.625	12.569	7.287	95.1%	96.4%	5.776	6.261	1,412,200	23,300	1,477,300
7 5/8"	26.40	L-80	25.560	0.328	6.969	6.844	7.549	7.780	90%	91.9%	6.925	5.051	954,700	14,950	1,071,700
7 5/8"	26.40	T-95	25.560	0.328	6.969	6.844	7.549	7.780	90%	91.9%	6.925	5.051	1,133,700	17,760	1,206,300
7 5/8"	26.40	P-110	25.560	0.328	6.969	6.844	7.549	7.780	90%	91.9%	6.925	5.051	1,312,700	20,560	1,425,900
7 5/8"	26.40	Q-125	25.560	0.328	6.969	6.844	7.549	7.780	90%	91.9%	6.925	5.051	1,491,700	23,370	1,560,500
7 5/8"	29.70	L-80	29.400	0.375	6.875	6.750	8.575	7.779	91.4%	92.9%	6.831	5.763	543,700	14,180	606,400
7 5/8"	29.70	T-95	29.400	0.375	6.875	6.750	8.575	7.779	91.4%	92.9%	6.831	5.763	645,600	16,830	683,700
7 5/8"	29.70	P-110	29.400	0.375	6.875	6.750	8.575	7.779	91.4%	92.9%	6.831	5.763	747,600	19,490	807,600
7 5/8"	29.70	Q-125	29.400	0.375	6.875	6.750	8.575	7.779	91.4%	92.9%	6.831	5.763	849,500	22,150	884,900
7 5/8"	33.70	L-80	33.040	0.430	6.765	6.640	9.758	7.828	92.4%	93.9%	6.721	5.541	624,500	14,330	696,500
7 5/8"	33.70	T-95	33.040	0.430	6.765	6.640	9.758	7.828	92.4%	93.9%	6.721	5.541	741,600	17,020	785,100
7 5/8"	33.70	P-110	33.040	0.430	6.765	6.640	9.758	7.828	92.4%	93.9%	6.721	5.541	856,700	19,710	927,700
7 5/8"	33.70	Q-125	33.040	0.430	6.765	6.640	9.758	7.828	92.4%	93.9%	6.721	5.541	975,800	22,400	1,015,500

ULT FS Summary



FS SUMMARY

www.tarponpipe.com

PIPE BODY								CONNECTION							
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	NOMINAL I.D.	DRIFT DIAMETER	AREA	TURNED O.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	BORED I.D.	THREAD LENGTH	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	?	in.	sq. in.	in.	%	%	?	in.	ft./lbs.	ft.	ft./lbs.
7 5/8"	39.00	L-80	38.050	0.500	6.625	6.500	11.237	7.927	94.6%	96.0%	6.581	6.082	718,800	14,500	801,700
7 5/8"	39.00	T-95	38.050	0.500	6.625	6.500	11.237	7.927	94.6%	96.0%	6.581	6.082	853,500	17,220	903,900
7 5/8"	39.00	P-110	38.050	0.500	6.625	6.500	11.237	7.927	94.6%	96.0%	6.581	6.082	988,300	19,940	1,067,700
7 5/8"	39.00	Q-125	38.050	0.500	6.625	6.500	11.237	7.927	94.6%	96.0%	6.581	6.082	1,123,100	22,660	1,170,000
7 5/8"	42.80	L-80	42.390	0.562	6.501	6.376	12.521	7.919	95.3%	96.9%	6.391	6.422	847,000	14,840	944,700
7 5/8"	42.80	T-95	42.390	0.562	6.501	6.376	12.521	7.919	95.3%	96.9%	6.391	6.422	1,005,800	17,620	1,065,200
7 5/8"	42.80	P-110	42.390	0.562	6.501	6.376	12.521	7.919	95.3%	96.9%	6.391	6.422	1,164,600	20,400	125,820
7 5/8"	42.80	Q-125	42.390	0.562	6.501	6.376	12.521	7.919	95.3%	96.9%	6.391	6.422	1,323,500	23,180	1,378,700
7 5/8"	45.30	L-80	44.670	0.595	6.435	6.310	13.194	7.918	95.6%	93.9%	6.391	6.422	951,200	14,950	1,060,900
7 5/8"	45.30	T-95	44.670	0.595	6.435	6.310	13.194	7.918	95.6%	93.9%	6.391	6.422	1,129,500	17,760	1,196,200
7 5/8"	45.30	P-110	44.670	0.595	6.435	6.310	13.194	7.918	95.6%	93.9%	6.391	6.422	1,307,900	20,530	1,413,000
7 5/8"	45.30	Q-125	44.670	0.595	6.435	6.310	13.194	7.918	95.6%	93.9%	6.391	6.422	1,485,200	23,370	1,548,300
7 5/8"	47.10	L-80	46.730	0.625	6.375	6.250	13.801	7.978	95.8%	97.1%	6.331	6.718	1,004,800	14,990	1,120,700
7 5/8"	47.10	T-95	46.730	0.625	6.375	6.250	13.801	7.978	95.8%	97.1%	6.331	6.718	1,193,200	17,800	1,263,700
7 5/8"	47.10	P-110	46.730	0.625	6.375	6.250	13.801	7.978	95.8%	97.1%	6.331	6.718	1,381,600	20,610	1,492,700
7 5/8"	47.10	Q-125	46.730	0.625	6.375	6.250	13.801	7.978	95.8%	97.1%	6.331	6.718	1,570,100	23,430	1,635,600
7 3/4"	46.10	L-80	45.470	0.595	6.560	6.500	13.429	8.054	94.2%	95.5%	65.390	6.147	1,053,100	15,020	1,174,600

ULT FS Summary



FS SUMMARY

www.tarponpipe.com

PIPE BODY								CONNECTION							
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	NOMINAL I.D.	DRIFT DIAMETER	AREA	TURNED O.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	BORED I.D.	THREAD LENGTH	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	?	in.	sq. in.	in.	%	%	?	in.	ft./lbs.	ft.	ft./lbs.
7 3/4"	46.10	T-95	45.470	0.595	6.560	6.500	13.429	8.054	94.2%	95.5%	65.390	6.147	1,250,600	17,840	1,324,500
7 3/4"	46.10	P-110	45.470	0.595	6.560	6.500	13.429	8.054	94.2%	95.5%	65.390	6.147	1,448,000	20,650	1,564,400
7 3/4"	46.10	Q-125	45.470	0.595	6.560	6.500	13.429	8.054	94.2%	95.5%	65.390	6.147	1,645,500	23,470	1,714,300
8 5/8"	28.00	L-80	27.020	0.304	8.017	7.892	7.978	8.802	92.0%	93.5%	7.976	5.650	1,007,800	14,770	1,122,800
8 5/8"	28.00	T-95	27.020	0.304	8.017	7.892	7.978	8.802	92.0%	93.5%	7.976	5.650	1,196,800	17,540	1,266,400
8 5/8"	28.00	P-110	27.020	0.304	8.017	7.892	7.978	8.802	92.0%	93.5%	7.976	5.650	1,382,700	20,370	1,495,700
8 5/8"	28.00	Q-125	27.020	0.304	8.017	7.892	7.978	8.802	92.0%	93.5%	7.976	5.650	1,574,700	23,080	1,639,300
8 5/8"	32.00	L-80	31.100	0.652	7.921	7.875	9.184	8.817	91.5%	93.0%	7.905	5.145	584,500	14,420	645,200
8 5/8"	32.00	T-95	31.100	0.652	7.921	7.875	9.184	8.817	91.5%	93.0%	7.905	5.145	694,100	17,120	729,600
8 5/8"	32.00	P-110	31.100	0.652	7.921	7.875	9.184	8.817	91.5%	93.0%	7.905	5.145	803,800	19,830	860,800
8 5/8"	32.00	Q-125	31.100	0.652	7.921	7.875	9.184	8.817	91.5%	93.0%	7.905	5.145	913,400	22,530	945,200
8 5/8"	36.00	L-80	35.140	0.400	7.825	7.700	10.376	8.782	91.2%	92.7%	7.781	5.381	669,900	14,360	739,500
8 5/8"	36.00	T-95	35.140	0.400	7.825	7.700	10.376	8.782	91.2%	92.7%	7.781	5.381	795,500	17,050	836,200
8 5/8"	36.00	P-110	35.140	0.400	7.825	7.700	10.376	8.782	91.2%	92.7%	7.781	5.381	921,100	19,740	986,600
8 5/8"	36.00	Q-125	35.140	0.400	7.825	7.700	10.376	8.782	91.2%	92.7%	7.781	5.381	1,046,800	22,430	1,083,300
8 5/8"	4.00	L-80	39.290	0.450	7.720	7.625	11.603	8.848	93.2%	94.6%	7.690	5.749	754,100	14,300	832,600
8 5/8"	4.00	T-95	39.290	0.450	7.720	7.625	11.603	8.848	93.2%	94.6%	7.690	5.749	895,500	16,980	941,400

ULT FS Summary



FS SUMMARY

www.tarponpipe.com

PIPE BODY								CONNECTION							
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	NOMINAL I.D.	DRIFT DIAMETER	AREA	TURNED O.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	BORED I.D.	THREAD LENGTH	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	?	in.	sq. in.	in.	%	%	?	in.	ft./lbs.	ft.	ft./lbs.
8 5/8"	4.00	P-110	39.290	0.450	7.720	7.625	11.603	8.848	93.2%	94.6%	7.690	5.749	1,036,900	19,670	1,110,800
8 5/8"	4.00	Q-125	39.290	0.450	7.720	7.625	11.603	8.848	93.2%	94.6%	7.690	5.749	1,178,300	22,350	1,219,600
8 5/8"	44.00	L-80	43.390	0.500	7.625	7.500	12.814	8.929	94.8%	96.2%	7.581	6.035	861,500	14,610	951,100
8 5/8"	44.00	T-95	43.390	0.500	7.625	7.500	12.814	8.929	94.8%	96.2%	7.581	6.035	1,023,100	17,350	1,075,400
8 5/8"	44.00	P-110	43.390	0.500	7.625	7.500	12.814	8.929	94.8%	96.2%	7.581	6.035	1,184,600	20,100	126,890
8 5/8"	44.00	Q-125	43.390	0.500	7.625	7.500	12.814	8.929	94.8%	96.2%	7.581	6.035	1,346,100	22,840	1,393,200
8 5/8"	49.00	L-80	47.990	0.557	7.511	7.386	14.175	8.939	96.6%	97.7%	7.467	6.127	967,700	14,860	1,068,200
8 5/8"	49.00	T-95	47.990	0.557	7.511	7.386	14.175	8.939	96.6%	97.7%	7.467	6.127	1,149,100	17,650	1,207,800
8 5/8"	49.00	P-110	47.990	0.557	7.511	7.386	14.175	8.939	96.6%	97.7%	7.467	6.127	1,330,500	20,440	1,425,100
8 5/8"	49.00	Q-125	47.990	0.557	7.511	7.386	14.175	8.939	96.6%	97.7%	7.467	6.127	1,512,000	23,230	1,564,800
8 5/8"	52.00	L-80	51.030	0.595	7.435	7.310	15.071	8.946	97.3%	98.6%	7.391	6.569	1,087,900	15,110	1,200,800
8 5/8"	52.00	T-95	51.030	0.595	7.435	7.310	15.071	8.946	97.3%	98.6%	7.391	6.569	1,291,900	17,940	1,357,900
8 5/8"	52.00	P-110	51.030	0.595	7.435	7.310	15.071	8.946	97.3%	98.6%	7.391	6.569	1,495,900	20,780	1,602,100
8 5/8"	52.00	Q-125	51.030	0.595	7.435	7.310	15.071	8.946	97.3%	98.6%	7.391	6.569	1,699,900	23,610	1,759,200
8 5/8"	54.00	L-80	53.400	0.625	7.375	7.250	15.771	8.951	97.8%	99.1%	7.331	6.912	1,167,900	15,250	1,289,100
8 5/8"	54.00	T-95	53.400	0.625	7.375	7.250	15.771	8.951	97.8%	99.1%	7.331	6.912	1,386,900	18,110	147,700
8 5/8"	54.00	P-110	53.400	0.625	7.375	7.250	15.771	8.951	97.8%	99.1%	7.331	6.912	1,605,900	20,970	1,719,900
8 5/8"	54.00	Q-125	53.400	0.625	7.375	7.250	15.771	8.951	97.8%	99.1%	7.331	6.912	1,824,900	26,840	1,888,500

ULT FS Summary



FS SUMMARY

www.tarponpipe.com

PIPE BODY								CONNECTION							
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	NOMINAL I.D.	DRIFT DIAMETER	AREA	TURNED O.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	BORED I.D.	THREAD LENGTH	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	?	in.	sq. in.	in.	%	%	?	in.	ft./lbs.	ft.	ft./lbs.
9 5/8"	40.00	L-80	38.940	0.395	8.835	8.700	11.499	9.816	93.8%	95.3%	8.805	5.427	1,228,500	15,330	1,355,500
9 5/8"	40.00	T-95	38.940	0.395	8.835	8.700	11.499	9.816	93.8%	95.3%	8.805	5.427	1,458,800	18,210	1,532,900
9 5/8"	40.00	P-110	38.940	0.395	8.835	8.700	11.499	9.816	93.8%	95.3%	8.805	5.427	1,689,200	21,080	1,808,600
9 5/8"	40.00	Q-125	38.940	0.395	8.835	8.700	11.499	9.816	93.8%	95.3%	8.805	5.427	1,919,500	23,960	1,986,000
9 5/8"	43.50	L-80	42.690	0.435	7.755	8.625	12.608	9.831	92.0%	93.4%	8.710	5.539	859,400	14,710	938,800
9 5/8"	43.50	T-95	42.690	0.435	7.755	8.625	12.608	9.831	92.0%	93.4%	8.710	5.539	1,020,600	17,470	1,064,700
9 5/8"	43.50	P-110	42.690	0.435	7.755	8.625	12.608	9.831	92.0%	93.4%	8.710	5.539	1,181,700	20,230	1,254,700
9 5/8"	43.50	Q-125	42.690	0.435	7.755	8.625	12.608	9.831	92.0%	93.4%	8.710	5.539	1,342,900	22,990	1,380,600
9 5/8"	47.00	L-80	46.140	0.472	8.681	8.525	13.626	9.819	97.2%	98.6%	8.626	6.020	923,800	14,420	1,009,400
9 5/8"	47.00	T-95	46.140	0.472	8.681	8.525	13.626	9.819	97.2%	98.6%	8.626	6.020	1,097,000	17,130	1,144,600
9 5/8"	47.00	P-110	46.140	0.472	8.681	8.525	13.626	9.819	97.2%	98.6%	8.626	6.020	1,270,300	19,830	134,900
9 5/8"	47.00	Q-125	46.140	0.472	8.681	8.525	13.626	9.819	97.2%	98.6%	8.626	6.020	1,443,500	22,540	1,484,200
9 5/8"	53.50	L-80	52.850	0.545	8.535	8.500	15.608	9.983	96.7%	98.1%	8.523	6.501	1,000,100	14,450	1,092,800
9 5/8"	53.50	T-95	52.850	0.545	8.535	8.500	15.608	9.983	96.7%	98.1%	8.523	6.501	1,187,600	17,150	1,239,100
9 5/8"	53.50	P-110	52.850	0.545	8.535	8.500	15.608	9.983	96.7%	98.1%	8.523	6.501	1,375,100	19,860	1,460,400
9 5/8"	53.50	Q-125	52.850	0.545	8.535	8.500	15.608	9.983	96.7%	98.1%	8.523	6.501	1,562,700	22,570	1,616,800
9 5/8"	58.40	L-80	57.380	0.595	8.435	8.375	16.947	9.968	97.2%	98.6%	8.414	6.381	1,212,500	15,160	1,313,500

ULT FS Summary



FS SUMMARY

www.tarponpipe.com

PIPE BODY								CONNECTION							
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	NOMINAL I.D.	DRIFT DIAMETER	AREA	TURNED O.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	BORED I.D.	THREAD LENGTH	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	?	in.	sq. in.	in.	%	%	?	in.	ft./lbs.	ft.	ft./lbs.
9 5/8"	58.40	T-95	57.380	0.595	8.435	8.375	16.947	9.968	97.2%	98.6%	8.414	6.381	1,428,000	18,010	1,489,600
9 5/8"	58.40	P-110	57.380	0.595	8.435	8.375	16.947	9.968	97.2%	98.6%	8.414	6.381	1,653,500	20,850	1,755,500
9 5/8"	58.40	Q-125	57.380	0.595	8.435	8.375	16.947	9.968	97.2%	98.6%	8.414	6.381	1,879,000	#####	1,931,600
9 7/8"	62.80	L-80	61.740	0.625	8.625	8.500	18.235	10.189	96.5%	97.8%	8.581	6.788	1,312,800	15,250	1,433,900
9 7/8"	62.80	T-95	61.740	0.625	8.625	8.500	18.235	10.189	96.5%	97.8%	8.581	6.788	1,558,900	18,110	1,626,100
9 7/8"	62.80	P-110	61.740	0.625	8.625	8.500	18.235	10.189	96.5%	97.8%	8.581	6.788	1,805,100	20,970	1,916,500
9 7/8"	62.80	Q-125	61.740	0.625	8.625	8.500	18.235	10.189	96.5%	97.8%	8.581	6.788	2,051,200	23,830	2,108,700
10 3/4"	40.50	L-80	38.880	0.350	10.050	9.894	11.480	10.919	92.0%	93.5%	9.995	5.392	841,600	14,430	908,600
10 3/4"	40.50	T-95	38.880	0.350	10.050	9.894	11.480	10.919	92.0%	93.5%	9.995	5.392	999,400	17,130	1,033,700
10 3/4"	40.50	P-110	38.880	0.350	10.050	9.894	11.480	10.919	92.0%	93.5%	9.995	5.392	1,157,200	19,840	1,216,800
10 3/4"	40.50	Q-125	38.880	0.350	10.050	9.894	11.480	10.919	92.0%	93.5%	9.995	5.392	1,315,000	22,540	1,341,900
10 3/4"	45.50	L-80	44.220	0.400	9.950	9.875	13.057	10.936	91.7%	93.1%	9.924	5.841	953,800	14,370	1,029,800
10 3/4"	45.50	T-95	44.220	0.400	9.950	9.875	13.057	10.936	91.7%	93.1%	9.924	5.841	1,132,700	17,070	1,171,700
10 3/4"	45.50	P-110	44.220	0.400	9.950	9.875	13.057	10.936	91.7%	93.1%	9.924	5.841	1,311,500	19,770	1,379,200
10 3/4"	45.50	Q-125	44.220	0.400	9.950	9.875	13.057	10.936	91.7%	93.1%	9.924	5.841	1,490,400	22,460	1,521,000
10 3/4"	51.00	L-80	49.500	0.450	9.850	9.694	14.618	10.954	91.9%	93.3%	9.795	5.731	1,070,200	14,410	1,155,600

ULT FS Summary



FS SUMMARY

www.tarponpipe.com

PIPE BODY								CONNECTION							
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	NOMINAL I.D.	DRIFT DIAMETER	AREA	TURNED O.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	BORED I.D.	THREAD LENGTH	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	?	in.	sq. in.	in.	%	%	?	in.	ft./lbs.	ft.	ft./lbs.
10 3/4"	51.00	T-95	44.220	0.400	9.950	9.875	14.618	10.954	91.9%	93.3%	9.795	5.731	1,270,900	17,110	1,314,700
10 3/4"	51.00	P-110	44.220	0.400	9.950	9.875	14.618	10.954	91.9%	93.3%	9.795	5.731	1,471,500	19,810	1,547,500
10 3/4"	51.00	Q-125	44.220	0.400	9.950	9.875	14.618	10.954	91.9%	93.3%	9.795	5.731	1,672,200	22,520	1,706,700
10 3/4"	55.50	L-80	49.500	0.450	9.850	9.694	16.010	10.958	93.0%	94.4%	9.705	6.340	1,186,500	14,590	1,281,100
10 3/4"	55.50	T-95	49.500	0.450	9.850	9.694	16.010	10.958	93.0%	94.4%	9.705	6.340	1,408,900	17,320	1,457,500
10 3/4"	55.50	P-110	49.500	0.450	9.850	9.694	16.010	10.958	93.0%	94.4%	9.705	6.340	1,631,400	20,060	1,715,600
10 3/4"	55.50	Q-125	49.500	0.450	9.850	9.694	16.010	10.958	93.0%	94.4%	9.705	6.340	1,853,900	22,790	1,892,000
10 3/4"	60.70	L-80	59.400	0.495	9.760	9.604	17.542	11.048	94.5%	95.9%	96.050	6.567	1,320,600	14,820	1,425,800
10 3/4"	60.70	T-95	59.400	0.495	9.760	9.604	17.542	11.048	94.5%	95.9%	96.050	6.567	1,568,200	17,600	1,622,200
10 3/4"	60.70	P-110	59.400	0.495	9.760	9.604	17.542	11.048	94.5%	95.9%	96.050	6.567	1,815,800	20,370	1,909,400
10 3/4"	60.70	Q-125	59.400	0.495	9.760	9.604	17.542	11.048	94.5%	95.9%	96.050	6.567	2,063,400	23,150	2,105,800
10 3/4"	65.70	L-80	64.530	0.545	9.660	9.504	19.058	11.099	96.8%	98.1%	9.539	6.322	1,469,600	15,180	1,586,300
10 3/4"	65.70	T-95	64.530	0.545	9.660	9.504	19.058	11.099	96.8%	98.1%	9.539	6.322	1,745,100	18,020	1,805,000
10 3/4"	65.70	P-110	64.530	0.545	9.660	9.504	19.058	11.099	96.8%	98.1%	9.539	6.322	2,020,700	20,870	2,124,500
10 3/4"	65.70	Q-125	64.530	0.545	9.660	9.504	19.058	11.099	96.8%	98.1%	9.539	6.322	2,296,200	23,720	2,343,100
11 3/4"	30.00	L-80	58.810	0.489	10.772	10.625	17.367	11.954	92.1%	93.5%	10.721	6.165	1,274,900	14,450	1,362,100
11 3/4"	30.00	T-95	58.810	0.489	10.772	10.625	17.367	11.954	92.1%	93.5%	10.721	6.165	1,514,000	17,160	1,554,400

ULT FS Summary



FS SUMMARY

www.tarponpipe.com

PIPE BODY								CONNECTION							
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	NOMINAL I.D.	DRIFT DIAMETER	AREA	TURNED O.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	BORED I.D.	THREAD LENGTH	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	?	in.	sq. in.	in.	%	%	?	in.	ft./lbs.	ft.	ft./lbs.
11 3/4"	30.00	P-110	58.810	0.489	10.772	10.625	17.367	11.954	92.1%	93.5%	10.721	6.165	1,753,000	19,870	1,827,500
11 3/4"	30.00	Q-125	58.810	0.489	10.772	10.625	17.367	11.954	92.1%	93.5%	10.721	6.165	1,992,100	22,580	2,019,700
11 3/4"	65.00	L-80	63.970	0.534	10.682	10.625	18.180	12.092	95.4%	96.8%	10.662	6.189	1,435,900	14,960	1,533,700
11 3/4"	65.00	T-95	63.970	0.534	10.682	10.625	18.180	12.092	95.4%	96.8%	10.662	6.189	1,705,100	17,760	1,750,300
11 3/4"	65.00	P-110	63.970	0.534	10.682	10.625	18.180	12.092	95.4%	96.8%	10.662	6.189	1,974,400	20,570	2,057,700
11 3/4"	65.00	Q-125	63.970	0.534	10.682	10.625	18.180	12.092	95.4%	96.8%	10.662	6.189	2,243,600	23,380	2,274,300
11 3/4"	71.00	L-80	69.420	0.582	10.583	10.430	20.500	12.070	96.7%	98.0%	10.531	6.358	1,578,900	15,160	1,686,300
11 3/4"	71.00	T-95	69.420	0.582	10.583	10.430	20.500	12.070	96.7%	98.0%	10.531	6.358	1,874,900	18,000	1,924,500
11 3/4"	71.00	P-110	69.420	0.582	10.583	10.430	20.500	12.070	96.7%	98.0%	10.531	6.358	2,171,000	20,840	2,262,500
11 3/4"	71.00	Q-125	69.420	0.582	10.583	10.430	20.500	12.070	96.7%	98.0%	10.531	6.358	2,467,000	23,690	2,500,700
11 7/8"	71.80	L-80	70.190	0.582	10.711	10.625	20.730	12.189	94.1%	95.4%	10.681	6.777	1,554,300	14,760	1,658,300
11 7/8"	71.80	T-95	70.190	0.582	10.711	10.625	20.730	12.189	94.1%	95.4%	10.681	6.777	1,845,700	17,530	1,893,100
11 7/8"	71.80	P-110	70.190	0.582	10.711	10.625	20.730	12.189	94.1%	95.4%	10.681	6.777	2,137,200	20,290	2,225,400
11 7/8"	71.80	Q-125	70.190	0.582	10.711	10.625	20.730	12.189	94.1%	95.4%	10.681	6.777	2,428,600	23,060	2,460,200
13 3/8"	61.00	L-80	59.450	0.430	12.515	12.359	17.550	13.603	93.9%	95.3%	12.460	5.657	1,313,100	14,720	1,378,200
13 3/8"	61.00	T-95	59.450	0.430	12.515	12.359	17.550	13.603	93.9%	95.3%	12.460	5.657	1,559,300	17,480	1,580,700

ULT FS Summary



FS SUMMARY

www.tarponpipe.com

PIPE BODY								CONNECTION							
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	NOMINAL I.D.	DRIFT DIAMETER	AREA	TURNED O.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	BORED I.D.	THREAD LENGTH	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	?	in.	sq. in.	in.	%	%	?	in.	ft./lbs.	ft.	ft./lbs.
13 3/8"	61.00	P-110	59.450	0.430	12.515	12.359	17.550	13.603	93.9%	95.3%	12.460	5.657	1,805,800	20,240	1,854,800
13 3/8"	61.00	Q-125	59.450	0.430	12.515	12.359	17.550	13.603	93.9%	95.3%	12.460	5.657	2,051,800	23,000	2,057,200
13 3/8"	68.00	L-80	66.100	0.480	12.415	12.259	19.521	13.594	93.4%	94.8%	12.360	6.210	1,453,000	14,650	1,525,200
13 3/8"	68.00	T-95	66.100	0.480	12.415	12.259	19.521	13.594	93.4%	94.8%	12.360	6.210	1,725,500	17,400	1,749,300
13 3/8"	68.00	P-110	66.100	0.480	12.415	12.259	19.521	13.594	93.4%	94.8%	12.360	6.210	1,997,900	20,150	2,052,600
13 3/8"	68.00	Q-125	66.100	0.480	12.415	12.259	19.521	13.594	93.4%	94.8%	12.360	6.210	2,704,000	22,790	2,276,600
13 3/8"	72.00	L-80	70.600	0.514	12.347	12.250	20.849	13.714	95.6%	97.1%	12.313	6.053	1,589,000	15,000	1,667,600
13 3/8"	72.00	T-95	70.600	0.514	12.347	12.250	20.849	13.714	95.6%	97.1%	12.313	6.053	1,869,000	17,810	1,912,600
13 3/8"	72.00	P-110	70.600	0.514	12.347	12.250	20.849	13.714	95.6%	97.1%	12.313	6.053	2,184,800	20,630	2,244,300
13 3/8"	72.00	Q-125	70.600	0.514	12.347	12.250	20.849	13.714	95.6%	97.1%	12.313	6.053	2,482,800	23,440	2,489,300
13 3/8"	77.00	L-80	75.333	0.550	12.275	12.119	22.247	13.706	96.5%	97.9%	12.220	6.382	1,710,600	15,130	1,794,400
13 3/8"	77.00	T-95	75.333	0.550	12.275	12.119	22.247	13.706	96.5%	97.9%	12.220	6.382	2,031,300	17,970	2,058,400
13 3/8"	77.00	P-110	75.333	0.550	12.275	12.119	22.247	13.706	96.5%	97.9%	12.220	6.382	2,352,100	20,810	2,415,100
13 3/8"	77.00	Q-125	75.333	0.550	12.275	12.119	22.247	13.706	96.5%	97.9%	12.220	6.382	2,672,800	23,650	2,679,100
13 3/8"	8.70	L-80	79.260	0.580	12.215	12.059	23.405	13.707	96.7%	98.1%	12.160	6.382	1,803,200	15,160	1,891,600
13 3/8"	8.70	T-95	79.260	0.580	12.215	12.059	23.405	13.707	96.7%	98.1%	12.160	6.382	2,141,300	18,010	2,169,800
13 3/8"	8.70	P-110	79.260	0.580	12.215	12.059	23.405	13.707	96.7%	98.1%	12.160	6.382	2,479,400	20,850	2,545,900
13 3/8"	8.70	Q-125	79.260	0.580	12.215	12.059	23.405	13.707	96.7%	98.1%	12.160	6.382	2,817,500	23,690	2,824,200

ULT FS Summary



FS SUMMARY

www.tarponpipe.com

PIPE BODY								CONNECTION							
NOMINAL O.D.	NOMINAL WEIGHT	GRADE	P.E. WEIGHT	WALL THICKNESS	NOMINAL I.D.	DRIFT DIAMETER	AREA	TURNED O.D	TENSILE EFFICIENCY	COMPRESSION EFFICIENCY	BORED I.D.	THREAD LENGTH	YIELD LOAD	REFERENCE DEPTH	PARTING LOAD
in.	lbs.	GRADE	lbs.	in.	?	in.	sq. in.	in.	%	%	?	in.	ft./lbs.	ft.	ft./lbs.
13 3/8"	75.00	L-80	82.910	0.608	12.159	12.003	24.482	13.711	96.8%	98.2%	12.104	6.699	1,889,200	15,190	1,981,900
13 3/8"	75.00	T-95	82.910	0.608	12.159	12.003	24.482	13.711	96.8%	98.2%	12.104	6.699	2,243,500	18,040	2,273,400
13 3/8"	75.00	P-110	82.910	0.608	12.159	12.003	24.482	13.711	96.8%	98.2%	12.104	6.699	2,597,700	20,890	2,667,400
13 3/8"	75.00	Q-125	82.910	0.608	12.159	12.003	24.482	13.711	96.8%	98.2%	12.104	6.699	2,952,000	23,730	2,959,000
13 3/8"	86.00	L-80	85.110	0.625	12.125	11.966	25.113	13.711	96.9%	98.3%	12.070	6.878	1,941,300	15,200	2,036,500
13 3/8"	86.00	T-95	85.110	0.625	12.125	11.966	25.113	13.711	96.9%	98.3%	12.070	6.878	2,305,300	18,050	2,336,000
13 3/8"	86.00	P-110	85.110	0.625	12.125	11.966	25.113	13.711	96.9%	98.3%	12.070	6.878	2,669,300	20,900	2,740,900
13 3/8"	86.00	Q-125	85.110	0.625	12.125	11.966	25.113	13.711	96.9%	98.3%	12.070	6.878	3,033,300	23,750	3,040,500
13 5/8"	88.20	L-80	86.780	0.625	12.375	12.250	25.626	13.970	96.9%	98.3%	12.331	6.823	1,979,200	15,200	2,070,600
13 5/8"	88.20	T-95	86.780	0.625	12.375	12.250	25.626	13.970	96.9%	98.3%	12.331	6.823	2,350,400	18,050	2,377,100
13 5/8"	88.20	P-110	86.780	0.625	12.375	12.250	25.626	13.970	96.9%	98.3%	12.331	6.823	2,721,500	20,900	2,788,200
13 5/8"	88.20	Q-125	86.780	0.625	12.375	12.250	25.626	13.970	96.9%	98.3%	12.331	6.823	3,092,600	23,750	3,094,700